



Designation: B111/B111M – 18a

Standard Specification for Copper and Copper-Alloy Seamless Condenser Tubes and Ferrule Stock¹

This standard is issued under the fixed designation B111/B111M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification² establishes the requirements for seamless tube and ferrule stock of copper and various copper alloys up to 3½ in. [80 mm] inclusive, in diameter, for use in surface condensers, evaporators, and heat exchangers. The following coppers and copper alloys are specified:³

Copper or Copper Alloy UNS No.	Previously Used Designation	Description
C10100	OFE	Oxygen-free electronic
C10200	OF ^A	Oxygen-free without residual deoxidants
C10300	...	Oxygen-free, extra low phosphorus
C10800	...	Oxygen-free, low phosphorus
C12000	DLP ^A	Phosphorized, low residual phosphorus
C12200	DHP ^A	Phosphorized, high residual phosphorus
C14200	DPA ^A	Phosphorized, arsenical
C15630	...	Nickel Phosphorus
C19200	...	Phosphorized, 1 % iron
C23000	...	Red Brass
C28000	...	Muntz Metal
C44300	...	Admiralty Metals, B, C, and D
C44400
C44500
C60800	...	Aluminum Bronze
C61300
C61400	...	Aluminum Bronze, D
C68700	...	Aluminum Brass, B
C70400	...	95-5 Copper-Nickel
C70600	...	90-10 Copper-Nickel
C70620	...	90-10 Copper-Nickel—Welding Grade
C71000	...	80-20 Copper-Nickel
C71500	...	70-30 Copper-Nickel
C71520	...	70-30 Copper-Nickel—Welding Grade

Copper or Copper Alloy UNS No.	Previously Used Designation	Description
C71640	...	Copper-nickel-iron-manganese
C72200

^A Designations listed in Classification B224.

1.2 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 The following safety hazards caveat pertains only to the test methods portion, Section 19, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. (Warning—Mercury has been designated by many regulatory agencies as a hazardous substance that can cause serious medical issues. Mercury, or its vapor, has been demonstrated to be hazardous to health and corrosive to materials. Use caution when handling mercury and mercury-containing products. See the applicable product Safety Data Sheet (SDS) for additional information. The potential exists that selling mercury or mercury-containing products, or both, is prohibited by local or national law. Users must determine legality of sales in their location.)*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents in the current issue of the *Annual Book of ASTM Standards* form a part of this specification to the extent referenced herein:

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.04 on Pipe and Tube.

Current edition approved Oct. 1, 2018. Published October 2018. Originally approved in 1937. Last previous edition approved in 2018 as B111/B111M-18. DOI: 10.1520/B0111_B0111M-18A.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SB-111 in Section II of the Code.

³ The UNS system for copper and copper alloys (see Practice E527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

*A Summary of Changes section appears at the end of this standard

2.2 ASTM Standards:⁴

- B153** Test Method for Expansion (Pin Test) of Copper and Copper-Alloy Pipe and Tubing
- B154** Test Method for Mercurous Nitrate Test for Copper Alloys
- B170** Specification for Oxygen-Free Electrolytic Copper—Refinery Shapes
- B224** Classification of Coppers
- B846** Terminology for Copper and Copper Alloys
- B858** Test Method for Ammonia Vapor Test for Determining Susceptibility to Stress Corrosion Cracking in Copper Alloys
- B968/B968M** Test Method for Flattening of Copper and Copper-Alloy Pipe and Tube
- E8/E8M** Test Methods for Tension Testing of Metallic Materials
- E29** Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E53** Test Method for Determination of Copper in Unalloyed Copper by Gravimetry
- E54** Test Methods for Chemical Analysis of Special Brasses and Bronzes (Withdrawn 2002)⁵
- E62** Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)⁵
- E75** Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys (Withdrawn 2010)⁵
- E76** Test Methods for Chemical Analysis of Nickel-Copper Alloys (Withdrawn 2003)⁵
- E112** Test Methods for Determining Average Grain Size
- E118** Test Methods for Chemical Analysis of Copper-Chromium Alloys (Withdrawn 2010)⁵
- E243** Practice for Electromagnetic (Eddy Current) Examination of Copper and Copper-Alloy Tubes
- E255** Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition
- E478** Test Methods for Chemical Analysis of Copper Alloys
- E527** Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)
- E2575** Standard Test Method for Determination of Oxygen in Copper and Copper Alloys (Withdrawn 2017)⁵

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms relating to copper and copper alloys, refer to Terminology **B846**.

4. Ordering Information

4.1 Include the following specified choices when placing orders for product under this specification, as applicable:

- 4.1.1 ASTM Designation and year of issue;
- 4.1.2 Copper or Copper Alloy UNS No. Designation (see **Table 1**);

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁵ The last approved version of this historical standard is referenced on www.astm.org.

- 4.1.3 Temper (Section 7);
- 4.1.4 Dimensions, outside diameter, and wall thickness, whether minimum or nominal (Section 14);
- 4.1.5 How furnished (tube or ferrule stock);
- 4.1.6 Quantity—total weight or total length or number of pieces of each size; and
- 4.1.7 Intended application.

4.2 The following options are available but may not be included unless specified at the time of placing of the order when required:

- 4.2.1 Tension Test per ASME Boiler and Pressure Vessel Code (see Section 8).
- 4.2.2 Hydrostatic or pneumatic test as an alternative to eddy current test (Section 13).
- 4.2.3 If the cut ends of the tubes do not need to be deburred (Section 15).
- 4.2.4 If the product is to be subsequently welded (**Table 1**, Footnotes G and H).
- 4.2.5 Residual Stress Test—Ammonia Vapor Test or Mercurous Nitrate Test (Section 12).
- 4.2.6 For Ammonia Vapor Test, risk level (pH value) if other than 10.
- 4.2.7 Heat identification or traceability details.
- 4.2.8 Certification (Section 23).
- 4.2.9 Test Report (Section 24).
- 4.2.10 If a subsequent thermal treatment after straightening is required (Section 7).
- 4.2.11 If product is purchased for agencies of the U.S. Government (see Supplementary Requirements section of this specification for additional requirements, if required).

5. Materials and Manufacture

5.1 Materials:

5.1.1 The material of manufacture shall be a form of such purity and soundness as to be suitable for processing into the products prescribed herein.

5.1.2 When specified in the contract or purchase order that heat identification or traceability is required, the purchaser shall specify the details desired.⁶

5.2 Manufacture:

5.2.1 The product shall be manufactured by such hot-working, cold-working, annealing, straightening, trimming, and other processes as to produce a uniform seamless tube in the finished product.

5.2.2 The product shall be hot- or cold-worked to the finished size, and subsequently annealed, when required, to meet the temper properties specified.

6. Chemical Composition

6.1 The product shall conform to the chemical composition requirements specified in **Table 1**.

⁶ Due to the discontinuous nature of the processing of castings into wrought products, it is not always practical to identify a specific casting analysis with a specific quantity of finished material.



TABLE 1 Chemical Requirements

Copper or Copper Alloy UNS No.	Composition, %											Other Named Elements	
	Copper	Tin	Aluminum	Nickel, incl Cobalt	Lead, max	Iron	Zinc	Manganese	Arsenic	Antimony	Phosphorus		Chromium
C10100	99.99 min ^A	0.0002 max	...	0.0010 max ^B	0.0005 max	0.0010 max	0.0001 max	0.00005 max	0.0005 max	0.0004 max	0.0003 max	0.0001 max	C
C10200 ^C	99.95 min ^D	C
C10300	99.95 min ^D	0.001–0.005
C10800	99.95 min ^D	0.005–0.012
C12000 ^E	99.90 min ^D	0.004–0.012
C12200	99.9 min ^D	0.015–0.040
C14200	99.4 min ^D	0.15–0.50	...	0.015–0.040
C15830	remainder	0.60–0.90 ^B	0.015–0.040
C19200	98.5 min	0.8–1.2	0.20 max	0.01–0.04
C23000	84.0–86.0	0.05	0.05 max	remainder
C28000	59.0–63.0	0.09	0.07 max	remainder
C44300	70.0–73.0	0.07	0.06 max	remainder	...	0.02–0.06
C44400	70.0–73.0	0.9–1.2	0.07	0.06 max	remainder
C44500	70.0–73.0	0.9–1.2	0.07	0.06 max	remainder	0.02–0.10
C60800	remainder ^D	...	5.0–6.5	...	0.10	0.10 max	0.02–0.35
C61300	remainder ^D	0.20–0.50	6.0–7.5	0.15 max	0.01	2.0–3.0	0.10 max	0.20 max	0.015 max	...	F, G
C61400	remainder ^D	...	6.0–8.0	...	0.01	1.5–3.5	0.20 max	1.0 max	0.015 max
C68700	76.0–79.0 ^D	...	1.8–2.5	...	0.07	0.06 max	remainder	...	0.02–0.06
C70400	remainder ^D	4.8–6.2	0.05	1.3–1.7	1.0 max	0.30–0.8
C70600	remainder ^D	9.0–11.0	0.05	1.0–1.8	1.0 max	1.0 max
C70820	86.5 min ^D	9.0–11.0	0.02	1.0–1.8	0.50 max	1.0 max	0.02 max	...	C.05 max S.02 max
C71000	remainder ^D	19.0–23.0	0.05 ^H	0.50–1.0	1.0 max ^H	1.0 max	H	...	H
C71500	remainder ^D	29.0–33.0	0.05	0.40–1.0	1.0 max	1.0 max
C71520	65.0 min ^D	29.0–33.0	0.02	0.40–1.0	0.50 max	1.0 max	0.02 max	...	C.05 max S.02 max C.06 max
C71640	remainder ^D	29.0–32.0	0.05 ^H	1.7–2.3	1.0 max ^H	1.5–2.5	H	...	S.03 max ^H
C72200	remainder ^D	15.0–18.0	0.05 ^H	0.50–1.0	1.0 max ^H	1.0 max	H	0.30–0.70	Si.03 max Ti.03 max ^H

^A This value is exclusive of silver and shall be determined by difference of "impurity total" from 100 %. "Impurity total" is defined as the sum of sulfur, silver, lead, tin, bismuth, arsenic, antimony, iron, nickel, mercury, zinc, phosphorus, selenium, tellurium, manganese, cadmium, and oxygen present in the sample.

^B Not including Cobalt.

^C Additional impurity maximums in percent for alloy C10100 shall be: bismuth 0.0001, cadmium 0.0005, selenium 0.0003, sulfur 0.0015, tellurium 0.0002, mercury 0.0001. For C10200, oxygen should be 0.0010 max.

^D Copper (including silver).

^E This includes oxygen-free Cu which contains P in an amount agreed upon.

^F Silicon shall be 0.10 % max.

^G When the product is for subsequent welding applications and is so specified by the purchaser, chromium shall be 0.05 % max, cadmium 0.05 % max, zinc 0.05 % max, and zirconium 0.05 % max.

^H When the product is for subsequent welding applications, and so specified by the purchaser, zinc shall be 0.50 % max, lead 0.02 % max, phosphorus 0.02 % max, sulfur 0.02 % max, and carbon 0.05 % max.