



Designation: B148 – 18

# Standard Specification for Aluminum-Bronze Sand Castings<sup>1</sup>

This standard is issued under the fixed designation B148; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification establishes requirements for sand castings produced from copper-base alloys having the alloy numbers,<sup>2</sup> commercial designations, and nominal compositions shown in [Table 1](#).

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

### 2.2 ASTM Standards:<sup>3</sup>

[B208 Practice for Preparing Tension Test Specimens for Copper Alloy Sand, Permanent Mold, Centrifugal, and Continuous Castings](#)

[B824 Specification for General Requirements for Copper Alloy Castings](#)

[B846 Terminology for Copper and Copper Alloys](#)

[E8/E8M Test Methods for Tension Testing of Metallic Materials](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.05 on Castings and Ingots for Remelting.

Current edition approved Oct. 1, 2018. Published October 2018. Originally approved in 1941. Last previous edition approved in 2014 as B148–14. DOI: 10.1520/B0148–18.

<sup>2</sup> The UNS system for copper and copper alloys (see Practice E527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

[E10 Test Method for Brinell Hardness of Metallic Materials](#)

[E18 Test Methods for Rockwell Hardness of Metallic Materials](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

## 3. Terminology

3.1 For definitions of terms related to copper and copper alloys, refer to Terminology [B846](#).

## 4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of Specification [B824](#).

## 5. Ordering Information

5.1 Include the following specified choices when placing orders for product under this specification as applicable:

5.1.1 ASTM designation and year of issue,

5.1.2 Copper or Copper Alloy UNS. No. designation,

5.1.3 Temper, must include optional Heat Treatment when needed,

5.1.4 Dimensions, diameter, and wall thickness (For tube or pipe: specify either O.D./I.D., O.D./Wall, or I.D./Wall unless standard size such as type K are ordered; for flat products: thickness, width, and edges; for rod, bar, or shapes: by diameter or distance between parallel surfaces),

5.1.5 Quantity of castings required,

5.1.6 Intended applications,

5.1.7 Specification title, number, and year of issue,

5.1.8 Pattern or drawing number and condition (cast, machined, and so forth),

5.1.9 Analysis of residual elements, if specified in the purchase order (Specification [B824](#)),

5.1.10 Pressure test requirements, if specified in the purchase order (Specification [B824](#)),

5.1.11 Soundness requirements, if specified in the purchase order (Specification [B824](#)),

5.1.12 Certification, if specified in the purchase order (Specification [B824](#)),

5.1.13 Test report, if specified in the purchase order (Specification [B824](#)),

5.1.14 Witness inspection, if specified in the purchase order (Specification [B824](#)),

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Nominal Compositions**

Copper Alloy UNS No.	Old Designation	Commercial Designation	Nominal Composition, %						
			Copper	Nickel	Iron	Aluminum	Silicon	Manganese	
C95200	9A	Grade A	88.0	...	3.0	9.0	...	...	
C95300 <sup>A</sup>	9B	Grade B	89.0	...	1.0	10.0	...	...	
C95400 <sup>A</sup>	9C	Grade C	85.0	...	4.0	11.0	...	...	
C95410 <sup>A</sup>	...	...	84.0	2.0	4.0	10.0	...	...	
C95500 <sup>A</sup>	9D	Grade D	81.0	4.0	4.0	11.0	...	...	
C95520 <sup>A</sup>	...	...	78.5	5.5	5.0	11.0	...	...	
C95600	9E	Grade E	91.0	...	...	7.0	2.0	...	
C95700	9F	Grade F	75.0	2.0	3.0	8.0	...	12.0	
C95800	...	...	81.3	4.5	4.0	9.0	...	1.2	
C95820	...	...	79.0	5.2	4.5	9.5	...	1.0	
C95900	...	...	87.5	...	4.5	13.0	...	...	

<sup>A</sup> These grades respond to heat treatment.

5.1.15 Approval of weld procedure and records of repairs, if specified in the purchase order (Section 10),

5.1.16 ASME Boiler and Pressure Vessel Code<sup>4</sup> application (12.2 and Section 14),

5.1.17 Castings for seawater service (6.2.3), and

5.1.18 Product marking, if specified in the purchase order (Specification B824).

5.2 When material is purchased for agencies of the U.S. Government, the Supplementary Requirements of this specification may be specified.

<sup>4</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

## 6. Materials and Manufacture

### 6.1 Materials:

6.1.1 The material of manufacture shall be sand castings of Copper Alloys, UNS No. C95200, C95300, C95400, C95410, C95500, C95520, C95600, C95700, C95800, C95820, C95900 of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 When specified in the contract or purchase order, that heat identification or traceability is required, the purchaser shall specify the details desired.

### 6.2 Manufacture:

6.2.1 As a specified option, Copper Alloy UNS Nos. C95300, C95400, C95410, C95500, and C95520 may be supplied in the heat-treated condition to obtain the higher

**TABLE 2 Mechanical Requirements**

Classification	Aluminum Bronze			Nickel Aluminum Bronze		Silicon Aluminum Bronze	Manganese- Nickel Aluminum Bronze	Nickel Aluminum Bronze	Aluminum Bronze
	As-Cast			As-Cast					
Copper Alloy UNS No.	C95200	C95300	C95400 and C95410	C95500	C95820	C95600	C95700	C95800 <sup>A</sup>	C95900 <sup>B</sup>
Tensile strength, min, ksi <sup>C</sup> (MPa <sup>D</sup> )	65 (450)	65 (450)	75 (515)	90 (620)	94 (650)	60 (415)	90 (620)	85 (585)	...
Yield strength, <sup>E</sup> min, ksi <sup>C</sup> (MPa <sup>D</sup> )	25 (170)	25 (170)	30 (205)	40 (275)	39 <sup>F</sup> (270) <sup>F</sup>	28 (195)	40 (275)	35 (240)	...
Elongation in 2 in. (50.8 mm), %	20	20	12	6	13	10	20	15	...
Brinell hardness No. <sup>G</sup> (3000-kg load)	110	110	150	190	...	...	...	...	...
Heat-Treated									
Copper Alloy UNS No.	C95300	C95400 and C95410	C95500	C95520 <sup>H</sup>					
Tensile strength, min, ksi <sup>C</sup> (MPa <sup>D</sup> )	...	80 (550)	90 (620)	110 (760)	125 (862)	...	...	...	...
Yield strength, <sup>E</sup> min, ksi <sup>C</sup> (MPa <sup>D</sup> )	...	40 (275)	45 (310)	60 (415)	95 <sup>F</sup> (655) <sup>F</sup>	...	...	...	...
Elongation in 2 in. (50.8 mm), %	...	12	6	5	2	...	...	...	...
Brinell hardness No. <sup>G</sup> (3000-kg load)	...	160	190	200	255 <sup>I</sup>	...	...	...	241 min

<sup>A</sup> As cast or temper annealed.

<sup>B</sup> Normally supplied annealed between 1100 and 1300 °F for 4 h followed by air cooling.

<sup>C</sup> ksi = 1000 psi.

<sup>D</sup> See Appendix X1.

<sup>E</sup> Yield strength shall be determined as the stress producing an elongation under load of 0.5 %, that is, 0.01 in. (0.254 mm) in a gage length of 2 in. (50.8 mm).

<sup>F</sup> Yield strength at 0.2 % offset, min, ksi<sup>C</sup> (MPa<sup>D</sup>).

<sup>G</sup> For information only.

<sup>H</sup> Copper Alloy UNS No. C95520 is used in the heat-treated condition only.

<sup>I</sup> Sand castings and sand cast test specimens shall be 25 HRC minimum.