



Designation: B248M – 22

Standard Specification for General Requirements for Wrought Copper and Copper- Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)¹

This standard is issued under the fixed designation B248M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification establishes the general requirements common to several wrought product specifications. Unless otherwise specified in the purchase order or in an individual specification, these general requirements shall apply to copper and copper-alloy plate, sheet, strip, and rolled bar supplied under each of the following product specifications issued by ASTM: [B36/B36M](#), [B96/B96M](#), [B103/B103M](#), [B121/B121M](#), [B122/B122M](#), [B130](#), [B152/B152M](#), [B169/B169M](#), [B422/B422M](#), [B534](#), [B694](#), [B888/B888M](#), and [B936](#).²

1.2 *Units*—This specification is the companion specification to inch-pound Specification [B248](#).

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:³

[B36/B36M](#) Specification for Brass Plate, Sheet, Strip, And Rolled Bar

[B96/B96M](#) Specification for Copper-Silicon Alloy Plate,

[Sheet, Strip, and Rolled Bar for General Purposes and Pressure Vessels](#)

[B103/B103M](#) Specification for Phosphor Bronze Plate, Sheet, Strip, and Rolled Bar

[B121/B121M](#) Specification for Leaded Brass Plate, Sheet, Strip, and Rolled Bar

[B122/B122M](#) Specification for Copper-Nickel-Tin Alloy, Copper-Nickel-Zinc Alloy (Nickel Silver), and Copper-Nickel Alloy Plate, Sheet, Strip, and Rolled Bar

[B130](#) Specification for Commercial Bronze Strip for Bullet Jackets

[B152/B152M](#) Specification for Copper Sheet, Strip, Plate, and Rolled Bar

[B169/B169M](#) Specification for Aluminum Bronze Sheet, Strip, and Rolled Bar

[B193](#) Test Method for Resistivity of Electrical Conductor Materials

[B248](#) Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

[B422/B422M](#) Specification for Copper-Aluminum-Silicon-Cobalt Alloy, Copper-Nickel-Silicon-Magnesium Alloy, Copper-Nickel-Silicon Alloy, Copper-Nickel-Aluminum-Magnesium Alloy, and Copper-Nickel-Tin Alloy Sheet and Strip

[B534](#) Specification for Copper-Cobalt-Beryllium Alloy and Copper-Nickel-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar

[B694](#) Specification for Copper, Copper-Alloy, Copper-Clad Bronze (CCB), Copper-Clad Stainless Steel (CCS), and Copper-Clad Alloy Steel (CAS) Sheet and Strip for Electrical Cable Shielding

[B820](#) Test Method for Bend Test for Determining the Formability of Copper and Copper Alloy Strip

[B846](#) Terminology for Copper and Copper Alloys

[B888/B888M](#) Specification for Copper Alloy Strip for Use in Manufacture of Electrical Connectors or Spring Contacts

[B936](#) Specification for Copper-Chromium-Iron-Titanium Alloy Plate, Sheet, Strip and Rolled Bar

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved May 1, 2022. Published May 2022. Originally approved in 1980. Last previous edition approved in 2017 as B248M – 17. DOI: 10.1520/B0248M-22.

² The UNS system for copper and copper alloys (see Practice [E527](#)) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

- [E8/E8M Test Methods for Tension Testing of Metallic Materials](#)
- [E18 Test Methods for Rockwell Hardness of Metallic Materials](#)
- [E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)
- [E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials](#)
- [E53 Test Method for Determination of Copper in Unalloyed Copper by Gravimetry \(Withdrawn 2022\)⁴](#)
- [E54 Test Methods for Chemical Analysis of Special Brasses and Bronzes \(Withdrawn 2002\)⁴](#)
- [E62 Test Methods for Chemical Analysis of Copper and Copper Alloys \(Photometric Methods\) \(Withdrawn 2010\)⁴](#)
- [E75 Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys \(Withdrawn 2010\)⁴](#)
- [E106 Test Methods for Chemical Analysis of Copper-Beryllium Alloys \(Withdrawn 2011\)⁴](#)
- [E112 Test Methods for Determining Average Grain Size](#)
- [E118 Test Methods for Chemical Analysis of Copper-Chromium Alloys \(Withdrawn 2010\)⁴](#)
- [E121 Test Methods for Chemical Analysis of Copper-Tellurium Alloys \(Withdrawn 2010\)⁴](#)
- [E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition](#)
- [E478 Test Methods for Chemical Analysis of Copper Alloys](#)
- [E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)
- [E1004 Test Method for Determining Electrical Conductivity Using the Electromagnetic \(Eddy Current\) Method](#)

3. Terminology

3.1 For definitions of terms related to copper and copper alloys, refer to Terminology [B846](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *lengths, mill, n*—straight lengths, including ends, that can be conveniently manufactured in the mills. Full length pieces are usually 2400 mm, 3000 mm, or 3600 mm and subject to established length tolerances.

3.2.1.1 *lengths, stock, n*—straight lengths that are mill cut and stored in advance of orders. They are usually 2400 mm, 3000 mm, or 3600 mm and subject to established length tolerances.

3.2.2 *rolled bar, n*—a rolled flat product over 5 mm thick and up to and including 300 mm wide, with sheared, sawed, or machined edges, in straight lengths or coils (rolls).

4. Materials and Manufacture

4.1 *Materials:*

4.1.1 The material of manufacture shall be a cast bar, cake, slab of such purity and soundness as to be suitable for processing into the products to the product specification listed in Section 1.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

4.1.2 When specified in the contract or purchase order that the heat identification or traceability is required, the purchaser shall specify the details desired.

4.2 *Manufacture:*

4.2.1 The product shall be manufactured by such hot-working, cold-working, and annealing process as to produce a uniform wrought structure in the finished product.

4.2.2 The product shall be hot- or cold-worked to the finished size and subsequently annealed, when required, to meet the temper properties specified.

4.3 *Edges*—The edges shall be slit, shared, sawed, or rolled edges, as specified. Slit edges shall be furnished unless otherwise specified in the contract or purchase order. See [5.6](#) for edge descriptions and corresponding tables for tolerances.

5. Dimensions, Mass, and Permissible Variations

5.1 *General*—For the purpose of determining conformance with the dimensional requirements prescribed in this specification, any measured value outside the specified limiting values for any dimension may be cause for rejection.

NOTE 1—Blank spaces in the tolerance tables indicate either that the material is not available or that no tolerances have been established.

5.2 *Thickness*—The standard method of specifying thickness shall be in decimal fractions of a millimetre. For material 0.50 mm and under in thickness, it is recommended that the nominal thicknesses be stated not closer than the nearest 0.01 mm. A list of preferred thicknesses is shown in [Appendix X1](#). The thickness tolerances shall be those shown in [Tables 1-3](#) for the product specification indicated:

5.2.1 [Table 1](#)—Thickness tolerances applicable to Specifications [B36/B36M](#), [B103/B103M](#), [B121/B121M](#), [B152/B152M](#), and [B888/B888M](#).

5.2.2 [Table 2](#)—Thickness tolerances applicable to Specifications [B96/B96M](#), [B122/B122M](#), [B169/B169M](#), [B422/B422M](#), and [B534](#).

5.2.3 [Table 3](#)—Special thickness tolerances applicable to Copper Alloy UNS No. C72500 when ordered to Specification [B122/B122M](#), and to Specification [B534](#) as noted in the table.

5.3 *Width*—The width tolerances shall be those shown in [Tables 4-6](#) depending on the type of edge required (see [5.3.1](#), [5.3.2](#), and [5.3.3](#)):

5.3.1 [Table 4](#)—Width tolerances for slit metal and slit metal with rolled edges.

5.3.2 [Table 5](#)—Width tolerances for square-sheared metal.

5.3.3 [Table 6](#)—Width tolerances for sawed metal.

5.4 *Length*—The material shall be furnished in coils or straight lengths of plate, sheet, strip, or rolled bar as specified. The length tolerances for straight lengths shall be those shown in [Tables 7-10](#) depending on the method of cutting required (see [5.4.1](#) – [5.4.4](#)). When ends are permitted, the length and quantity of the ends shall be in accordance with the schedule in [Table 8](#).

5.4.1 [Table 7](#)—Length tolerances for straight lengths.

5.4.2 [Table 8](#)—Schedule of minimum length and maximum weight of ends for mill lengths, specific lengths with ends, and stock lengths with ends.

TABLE 1 Thickness Tolerances

(Applicable to Specifications B36/B36M, B103/B103M, B121/B121M, B152/B152M, B888/B888M, and B936)

Thickness, mm		Thickness Tolerances, Plus and Minus, mm						
Over	Through	Strip			Sheet			
		Up to 200 mm, incl, in Width	Over 200 mm to 300 mm, incl, in Width	Over 300 mm to 600 mm, incl, in Width	Over 600 mm to 700 mm, incl, in Width	Over 700 mm to 900 mm, incl, in Width	Over 900 mm to 1200 mm, incl, in Width	Over 1200 mm to 1600 mm, incl, in Width
0.10	0.10	0.007	0.015
	0.20	0.01	0.02	0.03
0.20	0.30	0.015	0.025	0.035
0.30	0.40	0.02	0.03	0.045	0.06	0.08	0.09	0.10
0.40	0.50	0.025	0.035	0.05	0.06	0.08	0.09	0.11
0.50	0.60	0.03	0.04	0.05	0.08	0.09	0.10	0.12
0.60	0.70	0.035	0.05	0.06	0.08	0.09	0.10	0.12
0.70	1.0	0.045	0.05	0.06	0.09	0.10	0.12	0.15
1.0	1.3	0.05	0.06	0.07	0.10	0.12	0.15	0.17
1.3	2.0	0.06	0.07	0.08	0.12	0.15	0.17	0.20
2.0	3.5	0.07	0.08	0.10	0.15	0.17	0.20	0.25
3.5	5.0	0.08	0.10	0.11	0.17	0.20	0.25	0.30
Rolled Bar				Plate				
5.0	8.0	0.10	0.11	0.12	0.22	0.25	0.30	0.35
8.0	13.0	0.11	0.12	0.15	0.30	0.35	0.40	0.45
13.0	20.0	0.13	0.17	0.22	0.40	0.45	0.50	0.60
20.0	30.0	0.17	0.22	0.27	0.45	0.55	0.60	0.75
30.0	40.0	0.55	0.55	0.55	0.55	0.65	0.75	0.90
40.0	60.0	0.65	0.65	0.65	0.65	0.75	0.90	1.1

TABLE 2 Thickness Tolerances

(Applicable to Specifications B96/B96M, B122/B122M, B169/B169M, B422/B422M, and B534)

Thickness, mm		Thickness Tolerances, Plus and Minus, mm						
Over	Through	Strip			Sheet			
		Up to 200 mm, incl, in Width	Over 200 mm to 300 mm, incl, in Width	Over 300 mm to 600 mm, incl, in Width	Over 600 mm to 700 mm, incl, in Width	Over 700 mm to 900 mm, incl, in Width	Over 900 mm to 1200 mm, incl, in Width	Over 1200 mm to 1600 mm, incl, in Width
	0.10	0.01	0.02
0.10	0.20	0.015	0.025	0.035
0.20	0.30	0.02	0.03	0.05
0.30	0.40	0.025	0.035	0.06
0.40	0.50	0.03	0.05	0.06
0.50	0.60	0.035	0.06	0.07
0.60	0.70	0.05	0.06	0.07	0.10	0.13	0.15	0.18
0.70	1.0	0.06	0.07	0.08	0.13	0.15	0.18	0.20
1.0	1.3	0.07	0.08	0.10	0.15	0.18	0.20	0.25
1.3	2.0	0.08	0.10	0.11	0.18	0.20	0.25	0.30
2.0	3.5	0.10	0.11	0.12	0.20	0.25	0.30	0.35
3.5	5.0	0.11	0.13	0.15	0.25	0.30	0.35	0.40
Rolled Bar				Plate				
5.0	8.0	0.13	0.15	0.18	0.30	0.35	0.40	0.45
8.0	13.0	0.15	0.18	0.20	0.40	0.45	0.50	0.60
13.0	20.0	0.20	0.25	0.30	0.50	0.55	0.60	0.75
20.0	30.0	0.30	0.40	0.50	0.60	0.65	0.75	0.95
30.0	40.0	0.70	0.70	0.70	0.70	0.80	0.95	1.2
40.0	60.0	0.85	0.85	0.85	0.85	0.95	1.1	1.4

5.4.3 **Table 9**—Length tolerances for square-sheared metal in all widths 3000 mm and under.

5.4.4 **Table 10**—Length tolerances for sawed metal.

5.5 *Straightness*—The straightness tolerances which are the maximum edgewise curvature (depth of arc) in any 1800 mm portion of the total length, shall be those shown in **Tables 11-13** depending on the type of edge required.

5.5.1 **Table 11**—Straightness tolerances for metal as slit, or as slit and straightened, or as slit and edge-rolled, or metal with drawn edges.

5.5.2 **Table 12**—Straightness tolerances for square-sheared metal.

5.5.3 **Table 13**—Straightness tolerances for sawed metal.

5.6 *Edges*—When rolled edges are required, they may be produced by either rolling or drawing to one of the following specified edge contours:

5.6.1 *Square Edges (Square Corners)*—Edges shall have commercially-squared corners with a permissible maximum radius as prescribed in **Table 14**.