



Designation: B482 – 85 (Reapproved 2019)

Standard Practice for Preparation of Tungsten and Tungsten Alloys for Electroplating¹

This standard is issued under the fixed designation B482; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

Because of the high melting point of tungsten (3410 °C), this metal and its alloys are used in ultra-high-temperature applications. However, tungsten oxidizes readily and the oxides offer little or no protection to the metal because they melt or sublime below 2200 °C. Tungsten has a body-centered-cubic structure as does chromium. Its coefficient of thermal expansion is 4.3 $\mu\text{m}/\text{m} \cdot ^\circ\text{C}$; the coefficient of chromium is 6.1 $\mu\text{m}/\text{m} \cdot ^\circ\text{C}$, therefore, chromium-coated tungsten offers a reasonable match based on crystal structure and coefficient of thermal expansion. The effect of hydrogen must be considered in the design of coating systems for tungsten. Molecular hydrogen when trapped under a coating can result in failure of the part. Although failure can occur if the adhesion of the coating to the tungsten is inadequate, failure within the basis metal as rupture at laminations of stringers has been observed with off-grade tungsten.

1. Scope

1.1 This practice makes recommendations of several reported practices for electroplating on tungsten and its alloys along with comments as a guide in the selection of a processing method for a given application. Because data on methods and results of evaluation with electroplated coatings on tungsten are limited, a recommendation of one method over another cannot be made.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Processes

2.1 The several processes reported for electroplating on tungsten can be classified as either (1) providing as-deposited

adhesion of the coatings or (2) depending on diffusion alloy bonding to provide such adhesion. Appraisal of the relative merits of these processes depends on the application for the coating.

2.2 *Precleaning:*

2.2.1 The need for descaling, solvent cleaning, and alkaline-soak cleaning of tungsten is dictated by the degree of cleanliness of the surface to be coated. Remove gross scale and surface imperfections by mechanical means. Remove grease and oil by organic solvents. Remove saponifiable and dispersible surface dirt by soak cleaning in a hot alkaline cleaner.

2.2.2 Anodic treatment of tungsten surfaces in a 5 to 25 mass % sodium hydroxide solution at $71 \pm 6^\circ\text{C}$ and 16 to 25 A/dm^2 can be used to remove undesired surface metal. Anodic etching in a 10 mass % hydrofluoric acid electrolyte at $24 \pm 3^\circ\text{C}$ and 5.4 A/dm^2 can be used to remove light scale and undesired surface metal before activation and electroplating of tungsten.

2.3 *Activation and Electroplating*—Two alternative methods are presented below. The selection of one process over the other should be based on preliminary experimentation. Both procedures produce as-deposited adhesion of electroplated metals on tungsten.

2.3.1 *Methods I²*—Treat the precleaned tungsten in a hydrofluoric acid electrolyte (30 ± 10 mass % HF) at $24 \pm 3^\circ\text{C}$, using 2 to 5 V, 60 Hz ac, and 2 to 5 A/dm^2 for 1 to 2 min. Either

¹ This practice is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.02 on Pre Treatment.

Current edition approved April 1, 2019. Published April 2019. Originally approved in 1968. Last previous edition approved in 2013 as B482 – 85(2013). DOI: 10.1520/B0482-85R19.

² Cannizaro, J. J., U.S. Patent No. 2,433,651, June, 1948.