



Designation: B517 – 19

Standard Specification for Welded Nickel-Chromium-Iron-Alloy Pipe¹

This standard is issued under the fixed designation B517; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification² covers welded, cold-worked, and annealed nickel-chromium-iron alloy (UNS N06600,³ N06603, N06025, and N06045) pipe for general corrosive service and heat-resisting applications.

1.2 This specification covers outside diameter and nominal wall pipe shown in ANSI B36.19. Pipe having other dimensions may be furnished provided such pipe complies with all other requirements of this specification.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer; to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:⁴

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Nov. 1, 2019. Published December 2019. Originally approved in 1970. Last previous edition approved in 2014 as B517 – 05 (2014). DOI: 10.1520/B0517-19.

² For ASME Boiler and Pressure Code applications see related Specification SB-517 in Section II of that Code.

³ New designation established in accordance with ASTM E527 and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[B775 Specification for General Requirements for Nickel and Nickel Alloy Welded Pipe](#)

[B899 Terminology Relating to Non-ferrous Metals and Alloys](#)

2.2 *ANSI Standard:*

[B36.19 Stainless Steel Pipe](#)⁵

3. Terminology

3.1 Terms defined in Terminology B899 shall apply unless defined otherwise in this standard.

4. General Requirement

4.1 Material furnished in accordance with this specification shall conform to the applicable requirements of the current edition of Specification B775 unless otherwise provided herein.

5. Ordering Information

5.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory performance of material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

5.1.1 Alloy name or UNS number.

5.1.2 ASTM designation and year of issue.

5.1.3 Condition (temper).

5.1.4 *Dimensions:*

5.1.4.1 Nominal pipe size or outside diameter and schedule number or nominal wall thickness.

5.1.4.2 Length (specific or random).

5.1.5 Quantity (feet or metres, or number of pieces).

5.1.6 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished.

5.1.7 *Purchaser Inspection*—If the purchaser wishes to witness tests or inspection of material at the place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard