



Designation: C1069 – 09 (Reapproved 2022)

# Standard Test Method for Specific Surface Area of Alumina or Quartz by Nitrogen Adsorption<sup>1</sup>

This standard is issued under the fixed designation C1069; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the specific surface area of aluminas and silicas used in the manufacture of ceramics. The test method is a general one, permitting the use of any modern commercial nitrogen adsorption apparatus but strictly defining the outgassing procedure. Calculations are based on the Brunauer-Emmett-Teller (BET) equation.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

E173 Practice for Conducting Interlaboratory Studies of Methods for Chemical Analysis of Metals (Withdrawn 1998)<sup>3</sup>

## 3. Summary

3.1 An appropriate size sample is degassed for 1 h at 423 K before proceeding with the analysis as prescribed by the

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.04 on Raw Materials.

Current edition approved May 1, 2022. Published May 2022. Originally approved in 1986. Last previous edition approved in 2014 as C1069 – 09 (2014). DOI: 10.1520/C1069-09R22.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

manufacturer of the instrument used. The sample is accurately weighed after analysis.

3.2 Calculations are based on the BET equations, adapted where necessary for the equipment being used. The cross-sectional area of the nitrogen molecule is taken as 0.162 nm<sup>2</sup>.

## 4. Significance and Use

4.1 Both sellers and purchasers of alumina and quartz will find the test method useful to determine the specific surface area and indirectly as a measure of the particle size for material specifications, manufacturing control, and research and development.

## 5. Apparatus

5.1 *Specific Surface Area Analyzer*, recently (after 1970) manufactured commercial equipment employing low-temperature (77 K) nitrogen adsorption. This test method may be dynamic or static.

5.2 *Degassing Equipment*, suitable to the instrument used.

5.3 *Analytical Balance*, having a sensitivity of 1.0 mg.

## 6. Reagents and Materials

6.1 *Liquid Nitrogen*.

6.2 Cylinder of compressed nitrogen gas, high purity as specified by manufacturer, with pressure regulator.

6.3 Cylinder of compressed helium gas, high purity as specified by manufacturer, with pressure regulator, for static instruments or for dynamic instruments having gas mixing ability and employing the multipoint procedure or,

6.4 Cylinder of compressed, approximately 0.30 mol fraction, nitrogen in helium with pressure regulator, for other dynamic instruments employing the single point procedure.

## 7. Procedure

7.1 *Sample Preparation*—Blend the gross sample very well. For non-free-flowing materials mechanical agitation is necessary (for example, V-type blender with intensifier). If sample splitting of free-flowing materials is necessary, use a spinning riffler.

7.2 *Sample Degassing:*