



Designation: C113 – 14 (Reapproved 2019)

# Standard Test Method for Reheat Change of Refractory Brick<sup>1</sup>

This standard is issued under the fixed designation C113; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This test method covers the determination of the permanent linear change of refractory brick when heated under prescribed conditions.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

NOTE 1—Test methods incorporating additional provisions pertinent to specific refractory materials are given in the following Test Methods: C179, C210, and C605.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

C134 Test Methods for Size, Dimensional Measurements, and Bulk Density of Refractory Brick and Insulating Firebrick

C179 Test Method for Drying and Firing Linear Change of Refractory Plastic and Ramming Mix Specimens

C210 Test Method for Reheat Change of Insulating Firebrick

C605 Test Method for Reheat Change of Fireclay Nozzles

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.03 on Physical Properties.

Current edition approved Nov. 1, 2019. Published November 2019. Originally approved in 1934. Last previous edition approved in 2014 as C113 – 14. DOI: 10.1520/C0113-14R19.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

and Sleeves (Withdrawn 1997)<sup>3</sup>

E230/E230M Specification for Temperature-Electromotive Force (emf) Tables for Standardized Thermocouples

## 3. Significance and Use

3.1 Refractory brick and shapes of different compositions exhibit unique permanent linear changes after heating or reheating. This test method provides a standard procedure for heating various classes of refractories with appropriate heating schedules.

3.2 Linear reheat changes obtained by this test method are suitable for use in research and development, also often used to establish written specifications between producers and consumers.

3.3 Care should be exercised in selecting samples that are representative of the product being tested and that the schedule selected is appropriate to the product.

## 4. Apparatus

4.1 *Kiln*, of such design that the specified heating schedule and atmosphere can be maintained throughout the heating zone.

4.2 *Linear Measuring Device*, capable of being read to 0.02 in. (0.5 mm) over a span of 10 in. (254 mm). A hook-rule, as specified in Test Methods C134, a vernier caliper, or a dial gage device may be used.

4.3 *Gas Sampling and Analysis Equipment*, capable of determining the percent free oxygen and total combustibles in the atmosphere of the test chamber.

## 5. Test Specimens

5.1 For each test use three rectangular specimens measuring 9 by 4½ by 2½ or 3 in. (228 by 114 by 64 or 76 mm) in size, or, if smaller, shapes approaching these dimensions as closely as possible. These may be commercial brick of the specified size or test pieces cut out of larger shapes.

5.2 Using ceramic paint or crayon, label each specimen, and make a reference mark at each end on the center line of a broad

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.