



Designation: C1695 – 22

Standard Specification for Fabrication of Flexible Removable and Reusable Blanket Insulation for Hot Service¹

This standard is issued under the fixed designation C1695; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification addresses the minimum requirements for materials and fabrication of flexible removable and reusable blanket insulation for hot service, from above ambient temperatures to 1000°F (538°C).

1.2 This specification separately addresses industrial applications, outdoor commercial applications, and indoor commercial applications. Blanket insulation for industrial applications and outdoor commercial applications must be weather resistant and resistant to liquid chemicals. Blanket insulation for indoor commercial applications is limited to 500°F (260°C) maximum use temperature, is not required to be either weather resistant or resistant to chemicals, and is typically used for HVAC, plumbing, and other light grade indoor piping systems that distribute steam or water, or both.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.40 on Insulation Systems.

Current edition approved Oct. 1, 2022. Published October 2022. Originally approved in 2009. Last previous edition approved in 2020 as C1695 – 20. DOI: 10.1520/C1695-22.

2. Referenced Documents

2.1 *ASTM Standards:*²

- C168 Terminology Relating to Thermal Insulation
- C553 Specification for Mineral Fiber Blanket Thermal Insulation for Commercial and Industrial Applications
- C892 Specification for High-Temperature Fiber Blanket Thermal Insulation
- C1086 Specification for Glass Fiber Mechanically Bonded Felt Thermal Insulation
- C1129 Practice for Estimation of Heat Savings by Adding Thermal Insulation to Bare Valves and Flanges
- C1676 Specification for Microporous Thermal Insulation
- C1728 Specification for Flexible Aerogel Insulation
- D3389 Test Method for Coated Fabrics Abrasion Resistance (Rotary Platform Abrader)
- D3776/D3776M Test Methods for Mass Per Unit Area (Weight) of Fabric
- D3786/D3786M Test Method for Bursting Strength of Textile Fabrics—Diaphragm Bursting Strength Tester Method
- D5034 Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)
- D5035 Test Method for Breaking Force and Elongation of Textile Fabrics (Strip Method)
- D5189 Test Method for Temperature Corresponding To Vapor-Liquid Ratio Of 20 For Gasoline And Gasoline-Oxygenate Blends (Bomb Method) (Withdrawn 1993)³
- D5587 Test Method for Tearing Strength of Fabrics by Trapezoid Procedure
- D6413/D6413M Test Method for Flame Resistance of Textiles (Vertical Test)

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

2.2 Other Standards:

MIL-C-20079H Military Specification Cloth, Glass; Tape, Textile Glass and Thread, Glass and Wire Reinforced Glass⁴

3. Terminology

3.1 *General*—Definitions included in Terminology **C168** shall apply to the terms used in this specification.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *coated fabric, n*—A woven fabric coated with a rubber or plastic compound such that the woven fabric material itself is not exposed to the environment.

3.2.2 *commercial applications for removable blanket insulation, n*—applications of flexible removable/reusable blanket insulation that do not require high physical abuse resistance but do require protection from leaking water or steam, or both, such as might be found in HVAC or plumbing piping systems.

3.2.3 *D-ring, n*—a section of heavy wire which forms a complete loop in either a rectangular shape or the shape of the capital letter “D”, that is used in removable insulation blankets for attaching a fabric strap that secures the blanket around a pipe component or piece of equipment.

3.2.4 *hook and loop fastener, n*—a woven molded fabric material that has small hooks on one part and small loops on the other such that, when pressed together, they adhere to one another and further, requiring a significant force to separate one another.

3.2.5 *industrial applications for removable blanket insulation, n*—applications for flexible removable/reusable blanket insulation that require higher physical abuse resistance, protection from the weather and leaking chemicals, and can be exposed to outdoor conditions.

3.2.6 *lacing anchor, n*—a metal disk, located on the outside of an insulation blanket, that is secured to a pin that passes through the blanket; the assembly is used to wrap tire wire around so as to secure an insulation blanket around a pipe component or piece of equipment.

3.2.7 *lacing hook, n*—a metal hook that is located on the outside surface of an insulation blanket and that is secured through the blanket; tie wire is wrapped around it so as to secure an insulation blanket around a pipe component or piece of equipment.

3.2.8 *removable and reusable blanket insulation, n*—An insulation blanket, encased in woven fabric and/or woven wire mesh, that has attachment mechanisms designed to allow the assembly to be installed, then later removed and reinstalled, without using any new insulation or fabric materials.

4. Materials

4.1 Insulation shall be of a flexible fibrous material acceptable for the maximum temperature of the application. Acceptable materials must be one of the following:

4.1.1 High Temperature Fiber Blanket per Specification **C892**, any Type or Grade.

4.1.2 Needled Glass Fiber Mechanically Bonded Felt per Specification **C1086**.

4.1.3 Mineral Fiber Blanket, per Specification **C553**, of the Type suitable for the application.

4.1.4 Microporous Thermal Insulation, per Specification **C1676**, of the Type and Grade suitable for the application.

4.1.5 Flexible Aerogel Insulation, per Specification **C1728**, of the Type, Grade, and Category suitable for the application.

4.1.6 Alternative insulation materials shall only be used with design engineer/specifier or purchaser’s prior approval.

4.2 Material for the outer jacket, liner and straps, where used, shall be woven glass fiber cloth that has been treated with a water resistant compound, such as silicone rubber or polytetrafluoroethylene (PTFE), that is suitable for both interior and exterior use, and having the properties as shown in **Table 1**.

4.3 The Surface Temperature Limit for glass fiber fabric coated with Silicone rubber shall be a minimum of 500°F (260°C). The Surface Temperature Limit for glass fiber fabric coated with PTFE shall be a minimum of 600°F (315°C). Material for the inner jacket shall be the same as for the outer jacket for surface temperatures less than the selected material’s Surface Temperature Limit.

4.3.1 For surfaces exceeding the Surface Temperature Limits of either glass fiber fabric coated with Silicone rubber or PTFE up to 1000°F (538°C) where leaks of process fluids are not expected, the inner layer and gussets shall be one of the following, or in combination:

4.3.1.1 a plain, heat cleaned, glass fiber fabric,

4.3.1.2 a Type 304 stainless steel wire knitted mesh made from 0.008 in. (0.20 mm) diameter wire with nominal 6 to 8 openings per inch (25.4 mm).

4.3.2 For surfaces exceeding the Surface Temperature Limits of either glass fiber fabric coated with Silicone rubber or PTFE and where leaks of process fluids are expected, such as flange pairs and valves, the inner layer and gussets shall be as specified in 4.3.1 and 4.3.1.1 above but also with Type 304 stainless steel foil that has a minimum thickness of 0.001 in. (0.025 mm). This foil shall be placed between the hot surface and the insulation material.

4.4 All hardware such as D-rings, buckles, tags, quilting pins, lacing hooks and insulation anchors, etc. shall be made of Type 304 stainless steel. Where lacing hooks and lacing anchors are used, they shall be 12 or 14 Gauge.

4.5 Tie-Down Straps:

4.5.1 *Industrial Applications and Outdoor Commercial Applications*—These tie-down straps shall be constructed of the same material as the outer jacket with a double thickness and an edge trim sewn in place along both edges.

4.5.2 *Indoor Commercial Applications Only*—These tie-down straps shall be constructed either of the same materials as for applications specified in 4.5.1, or stand-alone hook and loop fastener materials with a minimum upper service temperature of 220°F (104°C). Minimum width of the hook and loop

⁴ Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, <http://quicksearch.dla.mil>.