



Standard Terminology of Ceramic Whitewares and Related Products¹

This standard is issued under the fixed designation C242; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology pertains to the terminology used in ceramic whitewares and related products.

1.2 Words adequately defined in standard dictionaries are not included. Included are words that are peculiar to this industry. Double words, hyphenated words, or phrases are listed alphabetically under the first word; additional important words are cross-referenced.

1.3 For definitions of terms relating to surface imperfections on ceramics, refer to Terminology F109.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D1129 Terminology Relating to Water

E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals (Withdrawn 2009)³

F109 Terminology Relating to Surface Imperfections on Ceramics

F465 Practice for Developing Precision and Accuracy Data on ASTM Method for the Analysis of Meat and Meat Products (Withdrawn 1993)³

2.2 British Standard:⁴

BS 2955 Glossary of Terms Relating to Powders

¹ This terminology is under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.01 on Editorial and Terminology.

Current edition approved Oct. 1, 2021. Published November 2021. Originally approved in 1950. Last previous edition approved in 2020 as C242 – 20b. DOI: 10.1520/C0242-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from British Standards Institution (BSI), 389 Chiswick High Rd., London W4 4AL, U.K., <http://www.bsigroup.com>.

3. Terminology

absolute or true density—see *absolute or true density* under **density**.

absorbance—the logarithm of that fraction of an incident light beam that is dissipated in the sample, being neither transmitted nor reflected.

absorbed moisture—water held mechanically in the material and having physical properties not substantially different from ordinary water at the same temperature and pressure.

absorption—(1) the relationship of the weight of the water absorbed by a ceramic specimen, subjected to prescribed immersion procedure, to the weight of the dry specimen; (2) the capacity of a substance to take up a substance, usually a liquid or gas, with the formation of an apparently homogeneous mixture.

adsorption—the capacity of a substance to accept and retain on its surface a layer of another substance, usually a gas or a liquid.

agglomerate—a jumbled mass or collection of two or more particles or aggregates, or a combination thereof, held together by relatively weak cohesive forces caused by weak chemical bonding or an electrostatic surface charge generated by handling or processing.

DISCUSSION—Common usage in powder technology (and British Standard BS 2955) has the terms “aggregate” and “agglomerate” interchanged in meaning from the definitions presented here, and care must be taken to determine in context which definition is in use.

aggregate—a dense mass of particles held together by strong intermolecular or atomic cohesive forces that is stable to normal mixing techniques, including high-speed stirring and ultrasonics.

alumina porcelain—see *alumina porcelain* under **porcelain**.

alumina whiteware—see *alumina whiteware* under **ceramic whiteware**.

andalusite—a polymorph, along with sillimanite and kyanite, of composition $Al_2O_3 \cdot SiO_2$ which on firing dissociates to yield principally mullite.

apparent or pycnometric density—see *apparent or pycnometric density* under **density**.

apparent porosity—see *apparent porosity* under **porosity**.

average particle size—a single value representing the entire particle-size distribution.

DISCUSSION—It is essential to specify the basis under which the average is obtained.

ball clay—a secondary clay, commonly characterized by the presence of organic matter, high plasticity, high dry strength, long vitrification range, and a light color when fired.

ball milling—a method of grinding and mixing material, with or without liquid, in a rotating cylinder or conical mill partially filled with grinding media such as balls or pebbles.

basalt ware—a black unglazed vitreous ceramic ware having the appearance of basalt rock.

Belleek china—a highly translucent whiteware composed of a body containing a significant amount of frit and normally having a luster glaze.

bentonite—a distinct type of fine-grained clay containing not less than 85 % montmorillonite clay having the formula $(\text{OH})_4\text{Si}_8\text{Al}_4\text{O}_{20}\text{nH}_2\text{O}$ and composed of units made up of two silica tetrahedral sheets with a central alumina octahedral sheet.

beryllium oxide (beryllia) (BeO)—an inorganic material of exceptionally high thermal conductivity which is toxic in the powder form.

bias—a constant or systematic error, as opposed to a random error, manifesting itself as a persistent positive or negative deviation of the method average from the accepted reference value. **E180; F465**

binder—a cementing medium; either a material added to the mixture to increase the green or dry strength as compacted, and which may be expelled during sintering or calcining, or a material added to a mixture for the purpose of cementing together particles.

DISCUSSION—A binder may be either a permanent addition, or a temporary additive to a ceramic product.

bisque fire—see *bisque fire* under **firing**.

blackbody—the ideal, perfect emitter and absorber of thermal radiation which emits radiant energy at the maximum rate possible, as a consequence of its temperature, and absorbs all incident radiation.

blistering—the development during firing of enclosed or broken macroscopic vesicles or bubbles in a body, or in a glaze or other coating.

bloating—substantial swelling produced by a heat treatment that causes the formation of a vesicular structure.

blunging—the wet process of blending, or suspending ceramic material in liquid by agitation.

body—the structural portion of a ceramic article, or the material or mixture from which it is made.

bone ash—calcined bone consisting essentially of calcium phosphate.

bone china—a translucent china made from a ceramic whiteware body composition containing a minimum of 25 % bone ash.

bright glaze—see *bright glaze* under **glaze**.

calcine—a ceramic material or mixture fired to less than fusion for use as a constituent in a ceramic composition.

capillary action—the phenomenon of intrusion of a liquid into interconnected small voids, pores, and channels in a solid, resulting from surface tension.

cassiterite (SnO₂)—an inorganic mineral of the tetragonal form used as a source of tin and tin oxide.

casting—a process for forming ceramic ware by introducing a body slip into a porous mold which absorbs sufficient water (or other liquid) from the slip to produce a semirigid article.

drain casting (hollow casting)—forming ceramic ware by introducing a body slip into an open porous mold, and then draining off the remaining slip when the case has reached the desired thickness.

solid casting—forming ceramic ware by introducing a body slip into a porous mold which usually consists of two major sections, one section forming the contour of the outside and the other forming the contour of the inside of the ware and allowing a solid cast to form between the two mold faces.

ceramic article—an article having a glazed or unglazed body of crystalline or partly crystalline structure, or of glass, which body is produced from essentially inorganic, nonmetallic substances and either is formed from a molten mass which solidifies on cooling, or is formed and simultaneously or subsequently matured by the action of the heat.

ceramic mosaic tile—an unglazed tile formed by either the dust-pressed or plastic method, usually $\frac{1}{4}$ to $\frac{3}{8}$ in. (6.4 to 9.5 mm) thick, and having a facial area of less than 6 in.² (39 cm²) and which is usually mounted on sheets approximately 1 by 2 ft (0.3 by 0.6 m) to facilitate setting.

DISCUSSION—Ceramic mosaic tile may be of either porcelain or natural clay composition and may be either plain or with an abrasive mixture throughout.

ceramic paste—a French term synonymous with “ceramic body.”

ceramic process—the production of articles or coatings from essentially inorganic, nonmetallic materials, the article or coating being made permanent and suitable for utilitarian and decorative purposes by the action of heat at temperatures sufficient to cause sintering, solid-state reactions, bonding, or conversion partially or wholly to the glassy state.

ceramic whiteware—a fired ware consisting of a glazed or unglazed ceramic body which is commonly white and of fine texture, designating such product classifications as tile, china, porcelain, semivitreous ware and earthenware.

alumina whiteware—any ceramic whiteware in which alumina (Al₂O₃) is an essential crystalline phase.

cordierite whiteware—any ceramic whiteware in which cordierite (2MgO·2Al₂O₃·5SiO₂) is the essential crystalline phase.

forsterite whiteware—any ceramic whiteware in which forsterite ($2\text{MgO}\cdot\text{SiO}_2$) is the essential crystalline phase.

steatite whiteware—any ceramic whiteware in which magnesium metasilicate ($\text{MgO}\cdot\text{SiO}_2$) is the essential crystalline phase.

titania whiteware—any ceramic whiteware in which titania (TiO_2) is the essential crystalline phase.

zircon whiteware—any ceramic whiteware in which zircon ($\text{ZrO}_2\cdot\text{SiO}_2$) is the essential crystalline phase.

ceramics—a general term applied to the art or technique of producing articles by a ceramic process, or to the articles so produced.

chemical porcelain—see *chemical porcelain* under **porcelain**.

china—a glazed or unglazed vitreous ceramic whiteware made by the china process and used for nontechnical purposes, designating such products as dinnerware, sanitary ware, and artware when they are vitreous. (See also **bone china**.)

china clay—see **kaolin**.

china process—the method of producing glazed ware by which the ceramic body is fired to maturity, following which the glaze is applied and matured by firing at a lower temperature.

china sanitary ware (sanitary plumbing fixtures)—glazed, vitrified whiteware fixtures having a sanitary service function.

chipping—the breaking off of a chip or flake from a ceramic body due primarily to the application of an external force.

clay—a natural mineral agglomerate, consisting essentially of hydrous aluminum silicates; plastic when sufficiently wetted, rigid when dried en masse, and vitrified when fired to a sufficiently high temperature.

clear glaze—see *clear glaze* under **glaze**.

closed porosity—see *closed porosity* under **porosity**.

coefficient of friction—the ratio of the parallel component of force required to overcome or have a tendency to overcome the resistance to relative motion of two surfaces in physical contact one with another, but otherwise unconstrained, to the normal component of the force; usually the force caused by gravity; applied through the object which tends to cause the friction.

color difference—(1) the magnitude and character of the difference between two colors, described by such terms as redder, bluer, lighter, darker, grayer, or cleaner; (2) the magnitude and direction of the difference between a sample and a standard, computed from tristimulus values, or chromaticity coordinates and luminance factor, by means of a specified set of color difference equations.

color space—a three dimensional arrangement for representing all possible colors; for example, in the color space defined by the color scales *L*, *a*, and *b* used to describe the color of opaque specimens, scale *L* is a measure of lightness, *a* is a measure of redness (plus) or greenness (minus), and *b* is a measure of yellowness (plus) or blueness (minus).

color standard—a plaque or other physical standard of established color value, against which standardization of an instrument is made.

DISCUSSION—It may be a reference standard at a calibration laboratory, a transfer standard used to calibrate a particular instrument, or a working standard for routine use.

comminution—the act or process of reduction of particle size with attendant increase in surface area and population of particles, usually but not necessarily by grinding, milling, or pulverizing.

conductive ceramic tile—tile made from special body compositions or by methods that result in specific properties of electrical conductivity while retaining other normal physical properties of ceramic tile.

connected porosity—see *connected porosity* under **porosity**.

cordierite porcelain—see *cordierite porcelain* under **porcelain**.

cordierite whiteware—see *cordierite whiteware* under **ceramic whiteware**.

corundum—a naturally occurring hexagonal mineral of the composition Al_2O_3 , which can also be prepared synthetically to high purity; noted for its hardness (9 on Mohs scale) and refractoriness (M.P. = 2045 °C).

DISCUSSION—It forms the gem varieties ruby and sapphire with appropriate impurities. It may contain associated minerals such as diaspore or various silicates, or both. Commonly coarsely crystalline, sometimes microcrystalline.

covering power—the ability of a glaze to cover the surface of the fired ware uniformly and completely.

crawling—a parting and contraction of the glaze on the surface of ceramic ware during drying or firing, resulting in unglazed areas bordered by coalesced glaze.

cracking—the cracking that occurs in fired glazes or other ceramic coatings as a result of tensile stresses; may also occur in the surface portion of uncoated (unglazed) whiteware bodies.

crystalline glaze—see *crystalline glaze* under **glaze**.

deagglomeration—the process of breaking down, usually by physical means, the masses of particles that are held together by relatively weak cohesive forces resulting in a final system of aggregates or primary particles, or both.

deairing—the process of removing entrapped air, or absorbed air from a mass or slurry, usually by application of a vacuum.

decorated—adorned, embellished, or made more attractive by means of color or surface detail.

decorating fire—see *decorating fire* under **firing**.

decoration:

inglaze decoration—a ceramic decoration applied on the surface of an unfired glaze and matured with the glaze.

overglaze decoration—a ceramic or metallic decoration applied and fired on the previously glazed surface of ceramic ware.

polychrome decoration—a multicolor decoration.