



Designation: C724 – 91 (Reapproved 2020)

Standard Test Method for Acid Resistance of Ceramic Decorations on Architectural- Type Glass¹

This standard is issued under the fixed designation C724; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers qualitative determination of the acid resistance of the ceramic decoration on architectural glass.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Terminology

2.1 Definitions:

2.1.1 *architectural glass, n*—glass used in the building industry.

3. Summary of Test Method

3.1 This test method qualitatively determines, by visual inspection, the degree of attack upon a ceramic decoration by a 10 % citric acid solution and a nominal 3.7 % hydrochloric acid solution.

4. Significance and Use

4.1 This test method evaluates the quality and serviceability of a ceramic decoration on architectural type glass. The degree of attack is determined using an acidic solution both quantitatively and qualitatively.

4.2 This test method provides a convenient control test during the manufacture of the ware.

4.3 This test method is suitable for specification acceptance.

5. Reagent

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.² Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 *Citric Acid Solution (1 + 9)*—Add ten parts by mass of reagent grade citric acid to 90 parts by mass of distilled water. Prepare fresh for each determination.

5.3 *Hydrochloric Acid Solution (1 + 9)*—Add ten parts by mass of reagent grade concentrated hydrochloric acid (HCl) (36 to 38 %) to 90 parts by mass of distilled water.

6. Procedure

6.1 Place four drops of each acid solution on a separate location on the surface of the ceramic decoration of the architectural glass to be tested. Cover each spot with a watchglass to retard evaporation and prevent contamination. Acid should remain on the surface of the test specimen for 15 min at 20 ± 2 °C.

6.2 After 15 min of exposure, wash the acid solutions (1 + 9) from the test specimen with tap water and allow it to air dry.

7. Report

7.1 Report the following information:

7.1.1 The degree of attack by visual observation by grading as follows:

¹ This test method is under the jurisdiction of ASTM Committee C14 on Glass and Glass Products and is the direct responsibility of Subcommittee C14.10 on Glass Decoration.

Current edition approved Aug. 1, 2020. Published September 2020. Originally approved in 1974. Last previous edition approved in 2015 as C724 – 91 (2015). DOI: 10.1520/C0724-91R20.

² *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.