



Designation: C774 – 88 (Reapproved 2021)

# Standard Test Method for Yield Strength of Enameling Steels After Straining and Firing<sup>1</sup>

This standard is issued under the fixed designation C774; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## INTRODUCTION

The strength after strain and fire of a steel is a significant factor in the strength of the final enameled ware. This test provides a method to quantify the yield strength of enamel steels after straining and firing by straining duplicate test plates to five different strain levels, exposing to a simulated enamel fire, and measuring the yield stress with a standardized tensile pull test.

### 1. Scope

1.1 This test method covers determination of the yield strength of steel specimens after simulated forming and enamel firing operations.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[E8 Test Methods for Tension Testing of Metallic Materials \[Metric\] E0008\\_E0008M](#)

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.12 on Materials for Porcelain Enamel and Ceramic-Metal Systems.

Current edition approved April 1, 2021. Published May 2021. Originally approved in 1974. Last previous edition approved in 2016 as C774 – 88(2016). DOI: 10.1520/C0774-88R21.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

### 3. Definition

3.1 *quarter lines*—imaginary lines parallel to the direction of rolling, positioned at a distance from the sheet mill edge equal to one quarter of the sheet width.

### 4. Summary of Test Method

4.1 Representative sheet-steel specimens are selected, strained in tension to simulate forming, heat treated to simulate enamel firing, and tension tested for determination of yield strength.

### 5. Significance and Use

5.1 In the manufacture of porcelain enameled ware, sheet steel is subjected to forming operations and subsequently to firing of the enamel at temperatures, typically, of 1400 to 1550 °F (760 to 844 °C). Some steels used for porcelain enameling are subject to grain growth in critically strained areas resulting in loss of strength.

5.2 This may lead to easy deformation of the steel and damage to the porcelain enamel coating.

5.3 This test method may be correlated with transit or use tests to evaluate the suitability of steel for porcelain enameled ware.

### 6. Apparatus

6.1 *Shear* for cutting blanks.

6.2 *Equipment* for cutting or machining tension specimens.

6.3 *Gage*, 2-in. (50.8-mm), for marking tension specimens.

6.4 *Tension-Testing Equipment*, as described in Test Methods and Definitions [A370](#).

6.5 *Specimen-Supporting Rack*, slotted to support specimens on edge spaced 1 in. (25.4 mm) apart.