



Designation: D3618 – 05 (Reapproved 2022)

Standard Test Method for Detection of Lead in Paint and Dried Paint Films¹

This standard is issued under the fixed designation D3618; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is intended as a screening test to determine if the solids in a paint contain more than 0.5 % lead. The test described barely detects the presence of 0.4 % but gives a definite positive result at the 0.5 % level.

NOTE 1—This test method may be used to detect the presence of lead at concentrations higher or lower than 0.5 % by making appropriate changes in the specimen size and reagent quantities specified.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 Paints giving an unexpected positive or questionable result should be analyzed quantitatively for lead, using Test Method [D3335](#).

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. Specific hazard statements are given in Section 7.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

- 2.1 *ASTM Standards:*²
[D1193 Specification for Reagent Water](#)
[D2832 Guide for Determining Volatile and Nonvolatile Content of Paint and Related Coatings](#)
[D3335 Test Method for Low Concentrations of Lead,](#)

[Cadmium, and Cobalt in Paint by Atomic Absorption Spectroscopy](#)

3. Summary of Test Method

3.1 The sample of liquid paint or dried film is prepared by dry ashing a weighed specimen at 475 °C to 500 °C. The ash is extracted with hot sodium hydroxide solution and a drop of the extract is transferred to filter paper. Lead present is oxidized to lead peroxide with bromine water, then treated with “tetrabase” to produce a blue quinoidal salt. Known amounts of lead are added to standard paints that are concurrently tested to provide a base for comparison.

4. Significance and Use

4.1 The permissible level of heavy metals in certain coatings is specified by governmental regulatory agencies. This test method provides a fully documented procedure for determining low concentrations of lead present in both water and solvent-reducible coatings to determine compliance.

5. Apparatus

- 5.1 *Burner*, Meker-type.
- 5.2 *Crucibles*, porcelain, high-form, 15-mL, with covers.
- 5.3 *Filter Paper*, ashless, medium texture.
- 5.4 *Hot Plate*, with variable surface temperature control over the range from 70 °C to 200 °C.
- 5.5 *Muffle Furnace*, maintained at 475 °C \pm 25 °C.
- 5.6 *Syringe*, glass, 2-mL.
- 5.7 *Volumetric Flasks*, 50, 100, 1000-mL.
- 5.8 *Paint Shaker*.
- 5.9 *Paint Draw-Down Bar*.

6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests unless otherwise specified. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are

¹ This test method is under the jurisdiction of ASTM Committee [D01](#) on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee [D01.21](#) on Chemical Analysis of Paints and Paint Materials.

Current edition approved Dec. 1, 2022. Published December 2022. Originally approved in 1977. Last previous edition approved in 2015 as D3618 – 05 (2015). DOI: 10.1520/D3618-05R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.