



Designation: D5657 – 07 (Reapproved 2023)

Standard Test Method for Fluid Tightness Ability of Adhesives Used on Threaded Fasteners¹

This standard is issued under the fixed designation D5657; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the ability of adhesives used for locking and sealing threaded fasteners, to make leak-tight assemblies.

1.2 The values stated in inch-pound units are to be regarded as the standard. The SI units given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D907 Terminology of Adhesives](#)

2.2 *SAE Standard:*

[SAE J429 Mechanical and Material Requirements for Externally Threaded Fasteners](#)³

2.3 *Federal Specification:*

[FF-N-836 Nut: Square, Hexagon, Cap, Slotted, Castle, Knurled, Welding and Single Ball Seat](#)⁴

¹ This test method is under the jurisdiction of ASTM Committee D14 on Adhesives and is the direct responsibility of Subcommittee D14.80 on Metal Bonding Adhesives.

Current edition approved Jan. 1, 2023. Published January 2023. Originally approved in 1995. Last previous edition approved in 2014 as D5657 – 07 (2014). DOI: 10.1520/D5657-07R23.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

⁴ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

3. Terminology

3.1 *Definitions:*

3.1.1 Many of the terms in this test method are defined in Terminology [D907](#).

4. Summary of Test Method

4.1 This test method consists of subjecting an adhesive-cured nut-and-bolt assembly to 50 psi pressure and determining the cured adhesive's ability to make the assembly leak-tight.

5. Significance and Use

5.1 Thread-locking adhesives are often used on threaded fasteners in sealing applications. This test method is used to determine an adhesive's ability to provide sealing capabilities under specified conditions.

6. Apparatus

6.1 *Test Fixture*, as shown in [Fig. 1](#), consisting of the following:

6.1.1 *Pressure Vessel*, provided with a means of filling with soapy water, capable of applying, withstanding, and measuring 50 psi (345 kPa) pressure of soapy water, and equipped with an air inlet and a gage for supplying and reading the pressure.

6.1.2 *Metal Plate*, flat, smooth approximately 1/2 in. (12.7 mm) thick, drilled with a 3/8 in. (9.5 mm) hole at its center. The hole is counterbored 5/8 in. (15.9 mm) diameter by 1/16 in. (1.6 mm) deep. The metal plate is welded to the pressure vessel.

6.1.3 *Rubber O-Ring or Flat Rubber Gasket*, 5/8 in. (15.9 mm) outside diameter by 7/16 in. (11.1 mm) inside diameter by 3/32 in. (2.4 mm) thick.

6.1.4 *Metal Plate*, used as a means of pressing the nut of the adhesive-treated test specimen against the O-ring or gasket with sufficient force to prevent leakage between the top plate and the washer face of the test specimen nut.

6.1.5 *Studs and Nuts*, used to clamp the fixture.

7. Test Specimens

7.1 *Steel Bolts*—3/8 in. size, Grade 5, in accordance with SAE J429, having a minimum length of 1 in. (25.4 mm) with a hexagonal head. Use thread series Unified National Fine, 24