



Designation: E2206 – 21

Standard Test Method for Force Calibration of Thermomechanical Analyzers¹

This standard is issued under the fixed designation E2206; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes the calibration or performance confirmation of the electronically applied force signal for thermomechanical analyzers over the range of 0 N to 1 N.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- E4 Practices for Force Verification of Testing Machines
- E473 Terminology Relating to Thermal Analysis and Rheology
- E617 Specification for Laboratory Weights and Precision Mass Standards
- E831 Test Method for Linear Thermal Expansion of Solid Materials by Thermomechanical Analysis
- E1142 Terminology Relating to Thermophysical Properties
- E1363 Test Method for Temperature Calibration of Thermomechanical Analyzers
- E2113 Test Method for Length Change Calibration of Thermomechanical Analyzers

¹ This test method is under the jurisdiction of ASTM Committee E37 on Thermal Measurements and is the direct responsibility of Subcommittee E37.10 on Fundamental, Statistical and Mechanical Properties.

Current edition approved March 1, 2021. Published April 2021. Originally approved in 2002. Last previous edition approved in 2015 as E2206 – 11 (2015). DOI: 10.1520/E2206-21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E2161 Terminology Relating to Performance Validation in Thermal Analysis and Rheology

3. Terminology

3.1 The technical terms used in this standard are defined in Terminologies E473, E1142, and E2161 including *calibration, conformance, precision, relative standard deviation, repeatability, reproducibility, and thermomechanical analyzer.*

4. Summary of Test Method

4.1 The electronic force signal generated by a thermomechanical analyzer is compared to that exerted by gravity on a known mass. The thermomechanical analyzer may be said to be in conformance if the performance is within established limits, typically 1%. Alternatively, the force signal may be calibrated using a two-point calibration method.

5. Significance and Use

5.1 Most thermomechanical analysis experiments are carried out with some force applied to the test specimen. This force is often created electronically. It may be constant or changed during the experiment.

5.2 This method demonstrates conformance or calibrates the electronically applied force signal.

5.3 This method may be used for research and development, quality control, manufacturing or regulatory applications.

5.4 Other thermomechanical analyzer calibration functions include temperature by Test Method E1363 and length change by Test Method E2113.

6. Apparatus

6.1 *Thermomechanical Analyzer*—The essential instrumentation required to provide a minimum thermomechanical analysis or thermodilatometric capability for this method includes:

6.1.1 *Rigid Specimen Holder*, inert, low expansivity material [typically $<0.6 \mu\text{m}/(\text{m} \cdot \text{K})$] to center the specimen in the furnace and to fix the specimen to mechanical ground.

NOTE 1—Amorphous silica (quartz) is a commonly used material of construction. Materials of construction with greater expansivity may be used but shall be reported.

6.1.2 *Rigid (Expansion or Compression) Probe*, inert, low expansivity material [typically $<0.6 \mu\text{m}/(\text{m} \cdot \text{K})$] which contacts the specimen with an applied compressive force (see Note 1).