



Designation: E2293 – 19

Standard Practice for Drying of Metal Bearing Ores, Concentrates, and Related Metallurgical Materials for the Determination of Mercury¹

This standard is issued under the fixed designation E2293; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This practice covers the sample drying step for the determination of mercury in ores, concentrates, and related metallurgical materials.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials](#)

[E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials](#)

[E877 Practice for Sampling and Sample Preparation of Iron Ores and Related Materials for Determination of Chemical Composition and Physical Properties](#)

[E882 Guide for Accountability and Quality Control in the Chemical Analysis Laboratory](#)

¹ This practice is under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee E01.02 on Ores, Concentrates, and Related Metallurgical Materials.

Current edition approved Oct. 1, 2019. Published October 2019. Originally approved in 2003. Last previous edition approved in 2013 as E2293–03(2013). DOI: 10.1520/E2293-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 Other Documents:³

[ISO 9599 Copper, Lead, and Zinc Sulfide Concentrates—Determination of Hygroscopic Moisture in the Analysis Sample-Gravimetric Method](#)

[ISO 12743 Copper, Lead, and Zinc Sulfide Concentrates—Sampling Procedures for the Determination of Metal and Moisture Content](#)

[ISO 10251 Copper, Lead, and Zinc Sulfide Concentrates—Determination of Mass Loss of Bulk Material on Drying](#)

3. Terminology

3.1 *Definitions*—For definitions of terms used in this Practice, refer to Terminology [E135](#).

4. Summary of Practice

4.1 Test samples to be used for mercury determination are dried at 60 °C.

5. Significance and Use

5.1 This practice is primarily to be used to dry samples for determination of total mercury. It should not be used for determination of sample moisture content. Most sample preparation methods prescribe drying samples at 105 °C, until a constant mass is obtained. The moisture content is determined as the percent mass loss on drying. Because mercury and some of its compounds are volatile at 105 °C, samples for mercury determination shall be dried at 60 °C (see Practice [E877](#), ISO 9599, ISO 12743, and ISO 10251).

5.2 It is assumed that all who use this practice will be trained analysts capable of performing skillfully and safely. It is expected that work will be performed in a properly equipped laboratory under appropriate quality control practices such as those described in Guide [E882](#).

6. Apparatus

6.1 *Drying Oven*, ventilated with forced circulation of air, regulated at a temperature of 60 °C ± 2 °C.

6.2 *Top-Loading Balance*, minimum precision of 0.01 %.

³ Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, Case postale 56, CH-1211, Geneva 20, Switzerland, <http://www.iso.ch>.