



Designation: E2808 – 21a

Standard Guide for Microspectrophotometry in Forensic Paint Analysis¹

This standard is issued under the fixed designation E2808; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

Color is one of the most important comparative characteristics of paints. The comparison of color is one of the first steps taken in a forensic paint comparison. Subjective terms such as “blue,” “violet,” or “purple” are descriptors of color but are inadequate for clear communication of color as terms could suggest different colors to different people. It is essential to note that this guide does not propose the use of instrumental color comparison for objects that are distinguishable to the eye. Since the 1940s, analytical instruments have been able to discriminate colors that the average human eye cannot distinguish. Microspectrophotometers (MSPs), in particular, allow for an objective measurement of the color of small, millimetre or submillimetre samples and are generally more sensitive than the more subjective results of visual microscopical color comparisons.

Suitable instruments with appropriate optics, sensitivity, resolution, and dynamic range can measure spectral curves from small samples as that light is transmitted, absorbed, reflected, or emitted (by means of fluorescence) by the sample. The spectral limits of different instruments can vary and can extend from the ultraviolet (UV) (~190 to 380 nm) through the visible spectral region (~380 to 780 nm) to the near infrared region (NIR) (~780 to 2500 nm). MSPs should not be confused with broadband or absorption filter-based tristimulus systems.

1. Scope

1.1 This guide is intended to assist forensic analysts who conduct UV, visible, NIR, or fluorescence emission spectral analyses on small fragments of paint or use Guide E1610, as this guide is to be used in conjunction with a broader analytical scheme.

1.2 This guide deals primarily with color measurements within the visible spectral range but will also include some details concerning measurements in the UV and NIR spectral ranges. The particular method(s) employed by each analyst depends upon available equipment, examiner training (Practices E2917, E3234), sample suitability, and sample size.

1.3 This guide provides basic recommendations and information about microspectrophotometers.

1.4 This guide does not address other areas of color evaluation such as colorimetric values, paint surface texture or pigment particle size, shape, or dispersion within a paint film that are evaluated by other forms of microscopy.

1.5 This guide is directed at the color analysis of commercially prepared paints and coatings. It does not address the analysis or determination of provenance of artistic, historical, or restorative paints, but it could be useful in those fields.

1.6 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.7 *This standard is intended for use by competent forensic science practitioners with the requisite formal education, discipline-specific training (see Practices E2917, E3234), and demonstrated proficiency to perform forensic casework.*

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

¹ This guide is under the jurisdiction of ASTM Committee E30 on Forensic Sciences and is the direct responsibility of Subcommittee E30.01 on Criminalistics. Current edition approved Sept. 1, 2021. Published September 2021. Originally approved in 2011. Last previous edition approved in 2021 as E2808 – 21. DOI: 10.1520/E2808-21A.

1.9 This international standard was developed in accordance with internationally recognized principles on standardization established in the *Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee*.

2. Referenced Documents

2.1 *ASTM Standards*:²

D16 Terminology for Paint, Related Coatings, Materials, and Applications

E179 Guide for Selection of Geometric Conditions for Measurement of Reflection and Transmission Properties of Materials

E275 Practice for Describing and Measuring Performance of Ultraviolet and Visible Spectrophotometers

E284 Terminology of Appearance

E1610 Guide for Forensic Paint Analysis and Comparison

E1492 Practice for Receiving, Documenting, Storing, and Retrieving Evidence in a Forensic Science Laboratory

E2917 Practice for Forensic Science Practitioner Training, Continuing Education, and Professional Development Programs

E3234 Practice for Forensic Paint Analysis Training Program

3. Terminology

3.1 *Definitions*—For definitions of paint-associated terminology used in this guide, see Terminologies **D16** and **E284**, Guide **E1610**, and Practice **E3234**.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *charge-coupled device (CCD), n*—a silicon-based semiconductor chip consisting of a linear or two-dimensional array of photo sensors or pixels that transfers an electrical charge and converts it into a digital value.

3.2.2 *effect pigment, n*—any paint pigment that is designed to produce a significant change in color attribute(s) in a paint film when the film is viewed or illuminated from varied angles.

3.2.3 *exclusionary difference, n*—a difference in a feature or property between compared items that is substantial enough to conclude that they did not originate from the same source.

3.2.3.1 *Discussion*—An exclusionary difference is statistically supported when an appropriate statistical analysis shows a result outside the range of what usually occurs when the items originate from the same source.

3.2.3.2 *Discussion*—When a statistical analysis is not suitable, an exclusionary difference can be determined by expert judgement.

3.2.4 *grating, n*—parallel set of linear, regularly repeating grooves that, when illuminated, produces dispersion of light into its requisite wavelengths with maxima and minima of light intensity as a consequence of interference.

3.2.4.1 *Discussion*—These maxima and minima vary in position with wavelength. This allows radiation of any given wavelength to be isolated from a mixture of wavelengths (for example, white light) and allows the grating to be used as part of a monochromator. The dispersion or ability to resolve separate wavelengths is expressed as the number of lines (or steps) in the grating per millimetre.

3.2.5 *measuring aperture, n*—element in the optical path of a MSP system that limits the area of illumination reaching the detector focal plane.

3.2.6 *metameric samples, n*—two or more samples that appear to have the same color under one type of illumination but can appear dissimilar under different lighting conditions, or two or more samples that appear to be the same color under all lighting conditions, yet their reflectance/transmittance spectral curves are different.

3.2.7 *microspectrophotometer (MSP), n*—a specialized spectrophotometer designed to measure the absorbance, reflectance and emission spectra of microscopic areas on samples.

3.2.8 *monochromator, n*—device designed to isolate narrow wavelength ranges of light from complex, broad-spectrum radiation.

3.2.9 *photomultiplier tube (PMT), n*—photosensitive vacuum tube device that quantitatively converts photons of light into electrical energy.

3.2.10 *pigment, n*—a finely ground, organic or inorganic, insoluble, and dispersed particle. Besides color, a pigment can provide many of the essential properties of paint, such as opacity, hardness, durability, and corrosion resistance (see also *effect pigment*).

3.2.11 *pixel binning, v*—the process of combining counts from adjacent pixels in a CCD detector during readout.

3.2.12 *spectral resolution, n*—measure of the ability to distinguish between adjacent peaks in a spectrum; it is usually determined by measuring peak width at half the maximum value of the peak height or full-width half-maximum (FWHM).

3.2.12.1 *Discussion*—Spectral resolution is not to be confused with spatial resolution (the smallest features that can be resolved in the field of view of the MSP camera or eyepieces or can be used to refer to the smallest spectral sampling area of the MSP).

4. Summary of Guide

4.1 One of the most obvious properties of paint is its color. Pigments are used in paint to modify color or other properties. The interaction of pigments with light is very complex with light being scattered, absorbed, reflected, and emitted by a paint layer. A MSP can measure reflected, transmitted, or emitted radiation over a range of wavelengths.

4.2 MSP is an integrated instrument consisting of a microscope, a light source, a spectrophotometer, and a data-processing device. The microscope not only allows for analysis location selection but also reflects or transmits light energy efficiently, uniformly, and reproducibly and images light onto the spectrophotometer entrance aperture. The spectrophotometer contains a dispersive element, most commonly a diffraction grating, and a detector. The system is designed to measure

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

the intensity of light energy with respect to its wavelength. All MSPs are single-beam instruments: a standard or a blank is measured, the result is stored, then a sample is measured and a ratio made to the standard to yield a transmittance or reflectance spectrum.

4.3 MSP analysis typically includes the visible spectral region (~380 to 780 nm), which captures information about the visual color of a sample. Most MSP systems are also sensitive to the NIR (~780 to 1100 nm). For UV-configured systems, the UV region (~190 to 380 nm) can provide additional information, for example, about UV absorbers in a clear coat layer. Furthermore, the spectrum of fluorescence emission (UV and visible excitation with UV to NIR emission) can also be captured.

4.4 MSP systems are generally used in forensic analysis because of the small sample sizes presented by paint film fragments. MSP is typically minimally destructive and microscopic samples can be analyzed. Instruments for color measurement from large samples can be used for color comparison, and can also be used for compiling color databases. Instruments for macroscopic color measurements produce results that are not necessarily directly comparable to MSP results.

4.5 Paint colors are usually measured in transmittance through thin sections. In transmittance measurements, a paint thin section is illuminated and the fraction of light transmitted or absorbed by the sample in the spectral range of interest (UV-Vis-NIR) is recorded relative to the light transmitted by a colorless background. Transmittance spectra can be plotted in either percent transmittance or absorbance.

4.6 In reflectance measurements of paint, a sample is illuminated and the fraction of light reflected from the sample in the spectral range of interest (UV-Vis-NIR) is recorded relative to the light reflected from a white reference standard. Reflectance spectral measurements are greatly affected by surface observation angle, surface texture, and the lack of microscopically reproducible diffuse reflectance standards. As a result, reflectance is seldom used for detailed color comparison, but it can be useful in exclusionary comparisons of bulk colors or for opaque samples. Reflectance spectra are plotted in percent reflectance.

5. Significance and Use

5.1 This guide is designed to assist an analyst in the selection of appropriate sample preparation methods and instrumental parameters for the analysis and comparison of paint pigments and colors. When used for comparison purposes, the goal is to determine whether any exclusionary differences exist between the samples.

5.2 Paint sample spectra can be measured by reflectance or transmittance spectroscopy for comparison purposes. Transmittance measurements are generally preferred and are required for the analysis of UV absorbers in clear coats and the detailed analysis of effect pigments that are not opaque. Emission comparison by means of fluorescence is also measurable.

5.3 It is not the intention of this guide to present comprehensive theories and methods of MSP. It is necessary that the

analyst have an understanding of UV-Vis-NIR MSP and general concepts of specimen preparation before using this guide. This information is available from manufacturers' reference materials, training courses, and references such as Eyring (1),³ Stoecklein (2), and Purcell (3).

6. Sample Preparation

6.1 The general collection, handling, and tracking of samples should meet or exceed the requirements of Practice E1492.

6.2 Verify that the work area and tools used for the preparation of samples are free of all extraneous materials that could transfer to the sample.

6.3 Transmittance Measurements:

6.3.1 Prepare hand-cut or microtome-cut thin sections for transmittance measurements. Although embedding followed by microtomy could be considered labor-intensive, this method (when questioned and known samples are mounted together) produces samples with an equivalent path length. Samples with equivalent path lengths are preferred for all transmission measurements and required for analysis of UV absorbers when the comparison relies upon differences in relative concentrations (4).

6.3.2 Paint sections of approximately 3 μm thick are generally appropriate for measurements of pigmented layers. Lightly colored samples or clear coats could require thicker sections (for example, up to 20 μm thick) (4, 5) for increased sensitivity of the instrument to low concentrations of UV absorbers or pigments.

6.3.3 Photometric reproducibility could be difficult to achieve with thin peels of paint layers or hand-cut cross sections due to uncontrolled path lengths within and between samples. This can lead to difficulties in the interpretation of shade (that is, intensity) differences when spectral curves do not exhibit exclusionary features.

6.4 Reflectance Measurements:

6.4.1 Conduct specular reflection measurements on clean and undamaged sample areas. Clean the surface of the sample carefully with deionized water, or alcohol if necessary. Reflectance measurements are usually conducted without further preparation of the sample surface so that surface features (for example, weathering) that might distinguish between samples are not altered. In some cases, it will be necessary to remove surface features. Surface weathering, for example, can be removed by polishing the paint using a diamond paste or another polishing medium so the measured properties of the surface are comparable to data for new, undamaged paint surfaces. However, caution is recommended before removal of features as the potential for other evidential loss increases. Retain a portion of the original unaltered sample whenever possible.

6.4.2 To obtain optimal results during spectral measurements, prepare the surface so it is free of scratches,

³ The boldface numbers in parentheses refer to a list of references at the end of this standard.