



Designation: E3112/E3112M – 20

Standard Test Method for Ballistic-resistant Products and Shoot Packs¹

This standard is issued under the fixed designation E3112/E3112M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This test method assesses resistance to complete penetration by projectiles and applies to ballistic-resistant products or shoot packs, either flexible or rigid, that are intended to provide protection against projectiles from small arms.² This test method does not assess blunt impact resistance.

1.2 This test method does not apply to body armor, armor panels, inserts, trauma packs, trauma plates, materials, or other items intended to be worn or located against the body to limit blunt trauma.

1.3 This test method applies only to products related to homeland security and public safety.

1.4 This test method is not intended to address architectural products covered by Test Method **F1233**, such as building materials and security glazing.

1.5 This test method is applicable to products or shoot packs that are constructed with identical layups of ballistic materials over the entire product or shoot pack. The product or shoot pack may have stitching, seams, or other joints.

NOTE 1—For example, this test method is applicable for evaluating a ballistic-resistant blanket constructed from multiple sheets of different materials laminated together; however, this test method is not applicable for evaluating a ballistic-resistant shield that has a discontinuity at the interface between opaque and transparent component materials.

1.6 The test method does not specify performance criteria or usage of the test results.

1.7 It is anticipated that this test method will be referenced by certifiers, purchasers, or other users in order to meet their specific needs.

1.7.1 In this test method, “other standards and specifications” and “unless specified elsewhere” refer to documents (for example, military standards, purchase specifications) that require the use of this test method. Purchasers and other users are

¹ This test method is under the jurisdiction of ASTM Committee E54 on Homeland Security Applications and is the direct responsibility of Subcommittee E54.04 on Personal Protective Equipment (PPE).

Current edition approved April 1, 2020. Published April 2020. Originally approved in 2018. Last previous edition approved in 2019 as E3112/E3112M – 19. DOI: 10.1520/E3112_E3112M-20.

² Small arms are defined as portable firearms, typically including handguns, shotguns, rifles, and light machine guns (Terminology E3005).

responsible for the “other standards and specifications” and for specifying any requirements that supersede those of this test method.

1.7.2 Purchasers and other users will specify the ballistic test threats, and the associated velocities, to be used.

1.8 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system are not necessarily exact equivalents; therefore, to ensure conformance with the standard, each system shall be used independently of the other, and values from the two systems shall not be combined.

1.8.1 The user of this standard will identify the system of units to be used, and it is critical to ensure that any cross-referenced standards maintain consistency of units between standards.

1.9 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.10 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards*:³

B211/B211M Specification for Aluminum and Aluminum-Alloy Rolled or Cold Finished Bar, Rod, and Wire

B221 Specification for Aluminum and Aluminum-Alloy Extruded Bars, Rods, Wire, Profiles, and Tubes

E3005 Terminology for Body Armor

E3062/E3062M Specification for Indoor Ballistic Test Ranges for Small Arms and Fragmentation Testing of Ballistic-resistant Items

E3078/E3078M Practice for Conditioning of Hard Armor Test Items

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

F1233 Test Method for Security Glazing Materials And Systems

2.2 Other Documents:

AATCC TM 169 Weather Resistance of Textiles: Xenon Lamp Exposure⁴

ISO/IEC 17025 General Requirements for the Competence of Testing and Calibration Laboratories⁵

MIL-STD-810G Test Method Standard for Environmental Engineering Considerations and Laboratory Tests⁶

ANSI/SAAMI Z299.1 Voluntary Industry Performance Standards for Pressure and Velocity of Rimfire Sporting Ammunition for the Use of Commercial Manufacturers⁷

ANSI/SAAMI Z299.2 Voluntary Industry Performance Standards for Pressure and Velocity of Shotgun Ammunition for the Use of Commercial Manufacturers⁷

ANSI/SAAMI Z299.3 Voluntary Industry Performance Standards for Pressure and Velocity of Centerfire Pistol and Revolver Ammunition for the Use of Commercial Manufacturers⁷

ANSI/SAAMI Z299.4 Voluntary Industry Performance Standards for Pressure and Velocity of Rifle Sporting Ammunition for the Use of Commercial Manufacturers⁷

3. Terminology

3.1 For terms not defined in this test method, the following definitions of Terminology E3005 apply: *armor panel, blunt impact resistance, body armor, cartridge, complete penetration, controlled ambient, fair hit, insert, obliquity, partial penetration, projectile, shot-to-edge distance, shot-to-shot distance, shoot pack, small arms, stop, strike face, test item, test item mounting system, test stand, test threat, trauma pack, trauma plate, unfair hit, witness panel, universal receiver, warmer rounds, and yaw.*

4. Summary of Test Method

4.1 The ballistic resistance of a product or shoot pack is determined by firing a series of test threats at each of a set of test items and assessing the number of partial penetrations and complete penetrations.

4.2 The performance requirements and test threats shall be specified in other standards and specifications.

NOTE 2—The performance requirements may be defined in terms of either: (1) The number of required fair hit impacts and the allowable number of complete penetrations, (2) The minimal acceptable calculated probability of a single impact being stopped and a corresponding confidence level. In this case, a minimum number of required fair hits may also be set, or (3) A combination of the above.

⁴ Available from American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27709-2215, <http://www.aatcc.org>.

⁵ Available from International Organization for Standardization (ISO), ISO Central Secretariat, BIBC II, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, <http://www.iso.org>.

⁶ Available from U.S. Government Printing Office, Superintendent of Documents, 732 N. Capitol St., NW, Washington, DC 20401-0001, <http://www.access.gpo.gov>.

⁷ Available from Sporting Arms and Ammunition Manufacturers' Institute, Flintlock Ridge Office Center, 11 Mile Hill Rd., Newtown, CT 06470-2359, www.saami.org.

5. Significance and Use

5.1 The test method is intended to determine the resistance to penetration of a ballistic-resistant product or shoot pack to specified projectiles impacting at specified velocities. No other properties of the ballistic-resistant product or shoot pack are evaluated by this test method.

5.2 This test method may be used by private-sector and government laboratories, manufacturers, research and development organizations, and others assessing the ballistic resistance of products or shoot packs or performing research and development of new products.

5.3 It is intended that this test method be referenced by other standards, specifications, or test methods.

6. Test Equipment and Apparatus

6.1 Test threats, and the associated velocities, shall be specified in other standards and specifications.

6.2 The ballistic test range shall meet the requirements of Specification E3062/E3062M.

6.3 The test item fixture, including position and attitude adjustments, shall be specified in other standards and specifications.

6.3.1 When not specified elsewhere, the test item mounting system shall be a frame as described below:

6.3.1.1 The frame shall consist of two layers of metal between which the test item is secured.

6.3.1.2 The frame shall be of sufficient size to restrain the test item during ballistic impact.

6.3.1.3 The frame, supports, clamps, and mounting fixtures shall be capable of securely retaining the test item and withstanding shock resulting from ballistic impact by the test projectiles. At a minimum, the clamps holding the test item in the frame shall be positioned in the center of each side of the frame or at the four corners of the frame.

6.4 The method for measuring projectile yaw may be with yaw cards, flash radiography, high speed video, or photography and shall be capable of determining, at the point of measurement, whether the angle of yaw is greater or less than 5°.

6.5 A witness panel shall be used to determine whether a complete penetration has occurred.

6.5.1 The witness panel outer dimensions shall be at least 305 mm by 305 mm [12 in. by 12 in.]. The height and width of the witness panel may be increased in order to allow for impact by all fragments resulting from projectile penetration.

6.5.2 For opaque test items, the witness panel shall be a sheet of 2024-T3, 2024-T4, or 5052 aluminum alloy⁸ and shall be nominally 0.50 mm [0.020 in.] thick.

6.5.3 For transparent test items, the witness panel shall be a 0.0254 mm [0.001 in.] thick sheet of aluminum foil.

⁸ Specifications B211/B211M and B221 contain information related to aluminum alloys.

7. Hazards

7.1 The ballistic tests described in this test method have inherent hazards. Adequate safeguards for personnel and property shall be employed when conducting these tests.

8. Sampling and Test Items

8.1 Test item details (including quantity, size, and required conditioning) shall be specified in other standards and specifications.

NOTE 3—A sufficient number of test items is required for testing, based on the conditioning requirements, anticipated total number of projectile impacts, and the number of projectile impacts that may be placed on each test item.

8.2 The supplier is responsible for providing the number of test items to accomplish the required testing. It is recommended that spare test items be provided.

8.2.1 When the use of a spare test item is required, details about selecting the appropriate spare test item shall be specified in other standards and specifications.

8.2.2 When not specified elsewhere and when the test item is either a shoot pack or a coupon representing a portion of the finished product, the size of each test item shall be at least 305 mm by 305 mm [12 in. by 12 in.].

NOTE 4—It is recommended that each test item that represents a product be the typical size and shape of that product.

9. Conditioning Procedures

9.1 This section describes conditioning procedures that may be applicable for ballistic-resistant products or shoot packs.

9.2 A thorough visual examination of each test item prior to and after the exposures shall be done to document any change in physical appearance resulting from the exposure.

9.3 Temperature Conditioning:

9.3.1 Place the test items into an environmental chamber preset to the initial conditions of Step 1 in Table 1.

9.3.1.1 For some products, not all steps in Table 1 are required. In those cases, other specifications will state the required steps.

9.3.2 Subject the test items to the conditions in Table 1. Each step transition shall take place and stabilize in less than 30 minutes.

TABLE 1 Exposure Conditions

Steps	Time (hours) (±5 minutes)	Temperature (°C) (±2°C [±4°F])	Relative Humidity (%) (±5 %)
1	2	25°C [77°F]	50
2	2	15°C [59°F]	N/A
3	2	5°C [41°F]	N/A
4	2	-5°C [23°F]	N/A
5	2	-15°C [5°F]	N/A
6	2	0°C [32°F]	N/A
7	2	15°C [59°F]	N/A
8	2	30°C [86°F]	50
9	2	45°C [113°F]	50
10	2	60°C [140°F]	50
11	2	75°C [167°F]	50
12	2	90°C [194°F]	50

NOTE 5—Exposure time includes the stabilization time.

9.3.3 Upon completion of the exposure protocol in Table 1, return the test items in the chamber to the initial conditions of Step 1 in Table 1.

9.3.4 Remove the test items from the environmental chamber.

9.3.5 Perform a thorough visual examination of each test item and document any change in physical appearance resulting from exposure.

9.4 Temperature Extremes Conditioning:

9.4.1 Tests shall be performed in accordance with constant temperature exposure procedures of MIL-STD-810G, Method 501.5, Procedure I (high temperature) and Method 502.5, Procedure I (low temperature).

9.4.2 One set of test items shall be subjected to high temperature, and another set shall be subjected to low temperature. Ramping of temperature is prohibited.

9.4.2.1 The starting temperature shall be controlled ambient.

9.4.2.2 One set of test items shall be heated in a chamber operating at 71.1°C ± 3°C [155°F ± 5°F] for a minimum of 6 h, not to exceed 7 h.

9.4.2.3 One set of test items shall be cooled in a chamber operating at -51.1°C ± 3°C [-60°F ± 5°F] for a minimum of 6 h, not to exceed 7 h.

9.5 Weathering Conditioning:

9.5.1 Weathering of test items shall be performed in accordance with AATCC Test Method 169 with the modifications listed below:

(1) The test apparatus shall be equipped with an automatic light monitor and shall be capable of automatically controlling irradiance, temperature, and humidity.

(2) The test items shall be positioned strike face toward the light source.

(3) The weathering cycle shall be a total of 180 minutes, consisting of the following in order: 40 minutes of light, 20 minutes of light with water spray on the test item, 60 minutes of light, and 60 minutes of darkness. The cycle shall be repeated until the total energy exposure is equal to 100 kJ/m², and the weathering cycle shall be terminated at that point.

(4) The spectral irradiance level shall be 0.55 ± 0.01 W/m²/nm bandpass at 340 nm.

(5) The temperatures and RH shall be as specified in Table 2.

9.5.2 After the required exposure period, the test items shall be removed from the apparatus.

TABLE 2 Temperatures for Weathering Procedure

	Dark Cycle	Light Cycle
Black Panel	38°C ± 3°C [100°F ± 5°F]	77°C ± 3°C [171°F ± 5°F]
Relative Humidity	≥95 %	50 % ± 5 % (This does not apply to light cycle with water spray.)