This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.



Designation: F105 - 72 (Reapproved 2019)

Standard Specification for Type 58 Borosilicate Sealing Glass¹

This standard is issued under the fixed designation F105; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers Type 58 borosilicate sealing glass for use in electronic applications.

Note 1—This specification is primarily intended to consider glass as most generally used, that is, glass in its transparent form as normally encountered in fabricating electronic devices. X1.3 refers to a sealing alloy that is compatible with this glass. Type 58 glass in other forms such as powdered, crushed, sintered, fibrous, etc., are excluded. The requirements of this specification, as applied to these forms, must be established in the raw glass prior to its conversion.

1.2 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

- C336 Test Method for Annealing Point and Strain Point of Glass by Fiber Elongation
- C338 Test Method for Softening Point of Glass
- C598 Test Method for Annealing Point and Strain Point of Glass by Beam Bending
- D150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulation
- D257 Test Methods for DC Resistance or Conductance of Insulating Materials
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E228 Test Method for Linear Thermal Expansion of Solid Materials With a Push-Rod Dilatometer
- F14 Practice for Making and Testing Reference Glass-Metal Bead-Seal

F15 Specification for Iron-Nickel-Cobalt Sealing Alloy

- F140 Practice for Making Reference Glass-Metal Butt Seals and Testing for Expansion Characteristics by Polarimetric Methods
- F144 Practice for Making Reference Glass-Metal Sandwich Seal and Testing for Expansion Characteristics by Polarimetric Methods

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

- 3.1.1 Form,
 - 3.1.2 Type of glass,
 - 3.1.3 Dimensions,
 - 3.1.4 Marking and packaging, and
 - 3.1.5 Certification (if required).

4. Chemical Composition

4.1 The typical chemical composition of this glass is as follows (Note 2):

	Weight %
Major Constituents:	
Silica (SiO ₂)	65.0
Alumina (Al ₂ O ₃)	7.5
Boron oxide (B ₂ O ₃)	18.0
Soda (Na ₂ O)	2.0
Potash (K ₂ O)	3.0
Barium oxide (BaO)	3.0
Minor Constituents:	
Lithium oxide (Li ₂ O)	0.6
Fluorine (F)	0.6, max
Reducible oxides (Note 3)	0.05, max

NOTE 2—Major constituents may be adjusted to give the desired electrical and physical properties to the glass. However, no change shall be made that alters any of these properties without due notification of, and approval by, the user.

Note 3—Total of arsenic trioxide (As_2O_3), antimony trioxide (Sb_2O_3), and lead oxide (PbO).

5. Physical Requirements

5.1 The material shall conform to the physical properties prescribed in Table 1. For electrical properties see Table 2, and its Footnote A.

6. Finish and Workmanship

6.1 The glass shall have a finish that ensures smooth, even surfaces and freedom from cracks, checks, bubbles, and other

¹ This specification is under the jurisdiction of ASTM Committee C14 on Glass and Glass Products and is the direct responsibility of Subcommittee C14.04 on Physical and Mechanical Properties.

Current edition approved Nov. 1, 2019. Published November 2019. Originally approved in 1968. Last previous edition approved in 2015 as F105 – 72 (2015). DOI: 10.1520/F0105-72R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.