This Research Report is issued under the fixed designation RR: C09-1053. You agree not to reproduce or circulate or quote, in whole or part, this document outside of ASTM International Committee/Society activities, or submit it to any other organization or standards body (whether national, international or other) except with the approval of the Chairman of the Committee having jurisdiction and the written authorization of the President of the Society. If you do not agree to these conditions, please immediately destroy all copies of this document. *Copyright ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428. All rights reserved.* 

## **15 December 2018**

## Committee C09 on Concrete and Concrete Aggregates Subcommittee C09.23 on Chemical Admixtures

Research Report: C09-1053

# Interlaboratory Study to Establish Precision Statements for ASTM C233, Standard Test Method for Air-Entraining Admixtures for Concrete

**Halogen Lamp-Based Method** 

#### **Technical contact:**

Willy Morrison Concrete Materials Laboratories Saint Paul, Minnesota 55114 United States 651-659-1333 wmorrison@amengtest.com

> ASTM International 100 Barr Harbor Drive West Conshohocken, PA 19428-2959

RR: C09-1053

#### 1. **Introduction:**

An Interlaboratory Study was conducted to establish a precision statement for C233, Standard Test Method for Air-Entraining Admixtures for Concrete.

#### 2. Test Method:

The Test Method used for this ILS is C233-18. To obtain a copy of C233-18, go to ASTM's website, <a href="www.astm.org">www.astm.org</a>, or contact ASTM Customer Service by phone at 610-832-9585 (8:30 a.m. - 4:30 p.m. Eastern U.S. Standard Time, Monday through Friday) or by email at <a href="mailto:service@astm.org">service@astm.org</a>.

## 3. Participating Laboratories:

The following laboratories participated in this interlaboratory study:

BASF Corporation	GCP
23700 Chagrin Blvd.	62 Whittemore Avenue
Beachwood, OH 44122	Cambridge, MA 02140
United States	United States

<b>Euclid Chemical Company</b>	SIKA
19218 Redwood Road	201 Polito Avenue
Cleveland, OH 44110	Lyndhurst, NJ 07071
United States	United States

## 4. Description of Samples:

There were 4 Air Entraining Admixtures of varying targeted results used for this study. Each sample was prepared and distributed by Willy Morrison of Concrete Materials Laboratory. Each participating laboratory supplied samples for distribution listed below.

#### Halogen Dryer Air Entraining Admixture Samples for Round Robin

Sample ID	Generic
T	alpha olefin sulfonate
X	sodium lauryl sulfate-vinsol based
Y	sodium dodecylbenzene sulfonate
Z	tall oil rosin

#### 5. Interlaboratory Study Instructions

Laboratory participants were emailed the test program instructions. For a copy of the instructions, please see Annex A.

RR: C09-1053

## 6. Description of Equipment/Apparatus<sup>1</sup>:

For information on the equipment/apparatus used by each laboratory, please see Annex B.

## 7. Data Report Forms:

Each laboratory was provided with a data report form for the collection of data. A copy of the data is provided in Annex C.

Please note: The laboratories have been randomly coded and cannot be identified herein.

#### 8. Statistical Data Summary:

A summary of the statistics calculated from the data returned by the participating laboratories is provided in Annex D.

#### 9. Precision and Bias Statement:

Precision and Bias of Halogen Lamp-Based Method

- 9.1 Precision:
- 9.1.1 The single-operator coefficient of variation of residue

by the halogen lamp-based method has been found to be

- 0.64 %. Therefore, the results of two properly conducted tests on the same material in the same laboratory on the same material by the same operator are not expected to differ by more than 1.8 % of their average.7
- 9.1.2 The multilaboratory coefficient of variation of resi- due by the halogen drying lamp-based method has been found to be 1.32 %. Therefore, the results of two properly conducted tests on the same material in different laboratories are not expected to differ by more than 3.7 % of their average.7
- 9.2 Bias—Because there is no accepted reference material suitable for determining the bias of this test method, no statement on bias is made.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this research report. Users of this research report are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This research report is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this research report may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or serviceastm.org (e-mail); or through the ASTM website (www.astm.org).

<sup>&</sup>lt;sup>1</sup> The equipment listed was used to develop a precision statement for C233-18. This listing is not an endorsement or certification by ASTM International.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.