

This Research Report is issued under the fixed designation RR: D16-2002. You agree not to reproduce or circulate or quote, in whole or part, this document outside of ASTM International Committee/Society activities, or submit it to any other organization or standards body (whether national, international or other) except with the approval of the Chair of the Committee having jurisdiction and the written authorization of the President of the Society. If you do not agree to these conditions, please immediately destroy all copies of this document. *Copyright ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428. All rights reserved.*

1 October 2020

**Committee D16 on Aromatic Hydrocarbons and Related Chemicals
Subcommittee D16.02 on Oxygenated Aromatics**

Research Report: D16-2002

**Interlaboratory Study to Establish Precision Statements for ASTM
D7883, Determination of 4-Carboxybenzaldehyde and p-Toluic
Acid in Purified Terephthalic Acid by Weak Anion Exchange High
Performance Liquid Chromatography**

Technical contact:

Yuhong Zhang
Analytical senior specialist SINOPEC
Shanghai, 201208 China
86-21-68462281
zhangyh.sshy@sinopec.com

ASTM International
100 Barr Harbor Drive
West Conshohocken, PA 19428-2959

Table of Contents

1. Introduction/ Background:	3
2. Test Method:.....	3
3. Participating Laboratories:	3
4. Description of Samples:	3
5. Interlaboratory Study Instructions.....	4
6. Description of Equipment/Apparatus:.....	4
7. Data Report Forms:	5
8. Statistical Data Summary:	5
9. Precision and Bias Statement:	5
Annex A: Statistical Data Summary.....	6
Annex B: Raw Data	7

1. Introduction/ Background:

This test method covers the determination of the 4-Carboxybenzaldehyde (4-CBA) and p-Toluic acid (p-TOL) in purified terephthalic acid (PTA) by weak anion exchange high performance liquid chromatography (HPLC). This method is applicable for 4-CBA from 2 to 500 mg/kg and for p-TOL from 10 to 500 mg/kg, respectively.

2. Test Method:

2.1 The Test Method used for this ILS is D7883-20. To obtain a copy of D7823, go to ASTM’s website, www.astm.org, or contact ASTM Customer Service by phone at 610-832-9585 (8:30 a.m. - 6:00 p.m. Eastern U.S. Standard Time, Monday through Friday) or by email at service@astm.org.

2.2 Weak Anion Exchange HPLC Method- PTA sample is dissolved in ammonium hydroxide solution. After pH adjustment, a fixed volume of this solution is injected into a high performance liquid chromatograph equipped with a UV detector. An anion-exchange column is used to separate the impurities 4-CBA and p-TOL from PTA. The external standard calibration is used for quantification.

3. Participating Laboratories:

The following laboratories participated in this interlaboratory study:

Shanghai Research Institute of Petrochemical Technology
Contact: Yuhong Zhang

SINOPEC Luoyang Engineering Co. LTD
Contact: Zhenguo Yang

PetroChina Wulumuqi Petrochemical Company
Contact: Guangshuo Yi

SINOPEC Tianjin Petrochemical Company
Contact: Jianzhong Liu

SINOPEC Yangzi Petrochemical Company
Contact: Daxi Ding

4. Description of Samples:

Five PTA samples with different concentrations of 4-CBA and p-TOL are tested in this study. The expected concentrations of the component interest are listed in Table 1

Table 1 Expected Concentrations of 4-CBA and p-TOL in PTA [mg/kg]

	Level I	Level II	Level III	Level IV	Level V
4-CBA	11	17	25.1	4~5	2
p-TOL	210	100	127.3	210	63