

**AEROSPACE
MATERIAL
SPECIFICATION**

SAE AMS3370

REV. B

Issued 1968-11
Revised 1988-04
Reaffirmed 2001-04
Stabilized 2012-01

Superseding AMS3370A

Silicone Resin, Elastomeric, Transparent
Room Temperature Cure

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE G-9, Aerospace Sealing Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3370B>**

FOREWORD

This Reaffirm contains format/editorial changes only.

1. SCOPE:

1.1 Form:

This specification covers a silicone resin in the form of a two-component liquid.

1.2 Application:

Primarily for encapsulation and conformal coating applications, where dielectric properties are important and a room temperature cure is desired.

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 Standards and Test Methods

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D 150 A-C Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulating Materials

ASTM D 412 Rubber Properties in Tension

ASTM D 746 Brittleness Temperature of Plastics and Elastomers by Impact

ASTM D 792 Specific Gravity (Relative Density) and Density of Plastics by Displacement

ASTM D 2240 Rubber Property - Durometer Hardness

2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Product shall consist of two parts; a colorless, transparent, liquid silicone resin and a separate catalyst which, when mixed in proper proportions, will cure at room temperature.

3.2 Properties:

Product shall conform to the following requirements; tests shall be conducted in accordance with specified ASTM methods, insofar as practicable, at $25\text{ }^{\circ}\text{C} \pm 1$ ($77\text{ }^{\circ}\text{F} \pm 2$) except as otherwise specified herein.

3.2.1 Uncatalyzed Resin:

3.2.1.1 Viscosity: Shall be 4000 - 7000 centipoises, determined using a Brookfield Viscometer, Type LVF, with a No. 4 spindle at 60 revolutions per minute.