

AEROSPACE MATERIAL SPECIFICATION

SAE AMS3659

REV. F

Issued	1966-03
Reaffirmed	1998-11
Revised	2010-05
Stabilized	2011-08
Superseding AMS3659E	

Polytetrafluoroethylene (PTFE) Extrusions
Premium Strength, Sintered and Stress-Relieved

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE AMS P, Polymeric Materials Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3659F>**

1. SCOPE

1.1 Form

This specification covers virgin, unfilled polytetrafluoroethylene (PTFE) in the form of extruded rods, tubes, and profiles.

1.2 These products have been used typically for parts, such as bushings and insulators, requiring better chemical inertness and dimensional stability up to 500 °F (260 °C) than AMS3657 and better mechanical and electrical properties than AMS3656, but usage is not limited to such applications. For applications such as bearings, seals, and back-up rings that do not require dielectric properties it is recommended to use AMS3678/1 Grade B.

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

1.4 Types 1 and 2, which were defined in previous revisions of this specification, have been combined. For documentation which specifies Type 1 or Type 2 of this specification, all of the requirements of this specification now apply.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS3656	Polytetrafluoroethylene Extrusions, Normal Strength, As Sintered
AMS3657	Polytetrafluoroethylene Extrusions, Premium Strength, As Sintered
AMS3678	Polytetrafluoroethylene (PTFE) Moldings and Extrusions, Unfilled, Pigmented and Filled Compounds

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM D 149	Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
ASTM D 792	Specific Gravity (Relative Density) and Density of Plastics by Displacement
ASTM D 4894	Polytetrafluoroethylene (PTFE) Granular Molding and Ram Extrusion Materials

3. TECHNICAL REQUIREMENTS

3.1 Material

The product shall be extruded from virgin PTFE powder in accordance with ASTM D 4894 Type IV or Type V without admixture of fillers, pigments, or adulterants, sintered, and stress-relieved.

3.1.1 Color

Shall be opaque white. Minor discolorations or contamination are acceptable, provided they do not have a detrimental effect on the finished product.

3.2 Properties

Extrusions shall conform to requirements shown in Table 1, Table 2, Table 3, Table 4, and 3.2.5; tests shall be performed on production extrusions and in accordance with specified test methods, insofar as practicable.

3.2.1 Tensile Strength at 73 °F ± 2 (23 °C ± 1)

Shall be as shown in Table 1, tested in accordance with 4.3.1.

TABLE 1 - MINIMUM TENSILE STRENGTH

Form	Nominal Diameter or Distance Between Parallel Sides Inches (Millimeters)	Tensile Strength Psi (MPa)
Rods, Profiles	Up to 0.500 (12.70), excl	1800 (12.4)
Rods, Profiles	0.500 to 1.500 (12.70 to 38.10), incl	1900 (13.1)
Rods, Profiles	Over 1.500 (38.10)	2000 (13.8)
Tubes	All sizes	1800 (12.4)