



AEROSPACE MATERIAL SPECIFICATION

AMS4474™

REV. B

Issued 2012-10
Revised 2021-09

Superseding AMS4474A

Aluminum Alloy, Sheet and Plate
4.0Cu - 1.0Li - 0.40Mg - 0.35Ag - 0.13Zr (2195-T8)
Solution Heat Treated, Cold Worked, and Artificially Aged
(Composition similar to UNS A92195)

RATIONALE

AMS4474B is the result of a Five-Year Review and update of this specification with changes to prohibit unauthorized exceptions (3.4.1.1, 3.7, 4.4.1, 5.1.1, 8.4), update references (2.1, 2.3, 3.2.1), allow use of SI testing for lot release (8.3), and allow the use of the immediate prior specification revision (8.5).

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of sheet and plate with a thickness of 0.125 to 0.499 inch (3.20 to 12.67 mm), inclusive (see 8.6).

1.2 Application

This product has been used for aircraft applications where it offers a combination of high strength and low density, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings

AMS2772 Heat Treatment of Aluminum Alloy Raw Materials

ARP1917 Clarification of Terms Used in Aerospace Metals Specifications

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2021 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS4474B/>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B660 Packaging/Packing of Aluminum and Magnesium Products

ASTM B666/B666M Identification Marking of Aluminum and Magnesium Products

2.3 ANSI Accredited Publications

Copies of these documents are available online at <http://webstore.ansi.org/>.

ANSI H35.1/H35.1M Alloy and Temper Designation Systems for Aluminum

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

Table 1 - Composition

Element	Min	Max
Silicon	--	0.12
Iron	--	0.15
Copper	3.7	4.3
Manganese	--	0.25
Magnesium	0.25	0.8
Zinc	--	0.25
Titanium	--	0.10
Silver	0.25	0.6
Lithium	0.8	1.2
Zirconium	0.08	0.16
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

Product shall be supplied in the following condition:

3.2.1 Solution heat treated, cold worked, and artificially aged to T8 temper (refer to ANSI H35.1/H35.1M).

3.3 Heat Treatment

Solution heat treatment and aging shall be performed in accordance with AMS2772.

3.4 Properties

The product shall conform to the following requirements determined in accordance with AMS2355 on the mill produced size.