



AEROSPACE MATERIAL SPECIFICATION

AMS4482™

REV. A

Issued 2012-07

Revised 2018-07

Superseding AMS4482

Cast Aluminum Alloy Composite
4.6Cu - 3.4Ti - 1.4B - 0.75Ag - 0.27Mg (205.0/TiB₂/3p-T7P)
Sand Cast, Solution, and Precipitation Heat Treated

RATIONALE

AMS4482A introduces Exceptions (3.9), revises Title, Chemical analysis standards (3.1), Condition (3.2), Microstructure and Particle Homogeneity (3.7), Quality (3.8.1) and Reports (4.5.1), and results from a Five-Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a dilute aluminum/TiB₂ metal matrix composite in the form of sand castings.

1.2 Application

These castings have been used typically for components requiring high strength and/or elevated temperature performance, but usage is not limited to such applications.

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2018 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback on this
Technical Report, please visit
<http://standards.sae.org/AMS4482A>**

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2175	Casting, Classification and Inspection of
AMS2360	Room Temperature Tensile Properties of Castings
AMS2694	In-Process Welding of Castings
AMS2771	Heat Treatment of Aluminum Alloy Castings
AMS2804	Identification Castings
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B557	Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
ASTM B557M	Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)
ASTM E29	Using Significant Digits in Test Data to Determine Conformance with Specifications
ASTM E155	Reference Radiographs for Inspection of Aluminum and Magnesium Castings
ASTM E716	Sampling and Sample Preparation of Aluminum and Aluminum Alloys for Determination of Chemical Composition by Spectrochemical Analysis
ASTM E1251	Analysis of Aluminum and Aluminum Alloys by Spark Atomic Emission Spectrometry
ASTM E1417/E1417M	Liquid Penetrant Testing
ASTM E1742/E1742M	Radiographic Examination
ASTM E3061	Analysis of Aluminum and Aluminum Alloys by Inductively Coupled Plasma Atomic Emission Spectrometry (Performance Based Method)

2.3 ANSI Accredited Publications

Copies of these documents are available online at <http://webstore.ansi.org>.

ANSI H35.1/ H35.1M Standard Alloy and Temper Designation System For Aluminum

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by spectrochemical methods in accordance with ASTM E1251 or ASTM E3061, or by other analytical methods acceptable to purchaser (see 3.4.1).

Table 1 - Composition

Element	Min	Max
Iron	--	0.08
Copper	4.2	5.0
Magnesium	0.20	0.33
Titanium ⁽¹⁾	3.0	3.85
Boron ⁽¹⁾	1.25	1.55
Silicon	--	0.10
Silver	0.6	0.9
Other Elements, each		0.08
Other Elements, total	--	0.17
Aluminum	remainder	

⁽¹⁾Titanium and Boron are present as TiB₂ reinforcement in the cast alloy matrix.

3.1.1 Test results may be rounded by the “rounding off” method of ASTM E29.

3.2 Condition

Solution and precipitation heat treated to the T7 temper (refer to ANSI H35.1/H35.1M).

3.3 Castings

Castings shall be produced from metal conforming to 3.1, determined by analysis of specimens cast as in 3.4.1.

3.4 Cast Test Specimens

Chemical analysis specimens and tensile specimens shall be cast as follows:

3.4.1 Chemical Analysis Specimens

Two specimens shall be cast from each melt. The first shall be taken after the last melt addition, and the second shall be after the last casting has been poured. Both specimens shall be tested to qualify the melt as in 3.1. Spectrochemical samples shall be prepared in accordance with ASTM E716.

3.4.2 Tensile Specimens

Shall be produced as follows:

3.4.2.1 Specimens Cut from a Casting and Specimens from Integrally Cast Coupons

Shall be removed after heat treatment, shall conform to ASTM B557 or ASTM B557M and shall be either 0.500 inch (12.70 mm) diameter at the reduced parallel gage section, standard sheet type specimens, or subsize specimens proportional to the standard as required by 3.6.1.

3.4.2.2 Separately Cast Specimens

Shall conform to ASTM B557 or ASTM B557M and shall be cast from each melt after the last melt additions. Specimens shall be cast in molds representing the mold used for castings. Chills are not permitted on test specimen cavity, except on the end face of the specimen when approved in accordance with 4.4.2.

3.5 Heat Treatment

Heat treatment shall conform to the requirements of AMS2771. Heat treatment parameters are proprietary.