



# AEROSPACE MATERIAL SPECIFICATION

AMS5629™

REV. J

Issued	1968-11
Reaffirmed	2006-10
Revised	2021-04

Superseding AMS5629H

Steel, Corrosion-Resistant, Bars, Wire, Forgings, Rings, and Extrusions  
13Cr - 8.0Ni - 2.2Mo - 1.1Al  
Vacuum Induction Plus Consumable Electrode Melted  
Solution Heat Treated, Precipitation Hardenable  
(Composition similar to UNS S13800)

## RATIONALE

AMS5629J prohibits unauthorized exceptions (3.9, 4.4.4, 5.2.1.1), revises composition (3.1) to replace obsolete chemical analysis standards, updates bar condition (3.3.1), updates heat treatment (3.4) adds strain rate control (3.5.2.2.1.1), adds machining allowance (3.6.2, 8.7), and results from a Five-Year Review and update of this specification.

### 1. SCOPE

#### 1.1 Form

This specification covers a premium aircraft-quality corrosion-resistant steel in the form of bars, wire, forgings, flash welded rings, and extrusions up to 12 inches (305 mm) in nominal diameter, or least distance between parallel sides in the solution heat treated condition (see 8.4), and stock of any size for forging, flash welded rings, or extrusion (see 8.8).

1.1.1 For purchase of solution treated and aged product, use the applicable AMS slash specification (see 8.4). If a slash sheet description is not specified, solution annealed material shall be supplied. A specific example of a slash specification is:

AMS5629/H1000 – Precipitation Hardened to H1000 condition

#### 1.2 Application

These products have been used typically for parts requiring corrosion resistance, stress-corrosion resistance, high strength up to 600 °F (316 °C), and good ductility and strength in the transverse direction in large section sizes, but usage is not limited to such applications.

1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking; ARP1110 recommends practices to minimize such conditions.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2021 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit  
<https://www.sae.org/standards/content/AMS5629J>

### 1.3 Classification

Product covered by this specification is classified as follows:

#### 1.3.1 Melting Practice

Type 1 - Steel multiple melted using vacuum consumable electrode remelting.

Type 2 - Steel multiple melted using electroslag remelting.

1.3.1.1 When a type is not specified, Type 1 shall be supplied.

#### 1.3.2 Maximum Delta Ferrite Content

Class A – 0.5% max., free ferrite.

Class B – 1.0% max., free ferrite.

Class C – 2.0% max., free ferrite.

1.3.2.1 When no class is specified, any class may be supplied.

## 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2241	Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS2248	Chemical Check Analysis Limits Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS2300	Steel Cleanliness, Premium Aircraft-Quality Magnetic Particle Inspection Procedure
AMS2315	Determination of Delta Ferrite Content
AMS2371	Quality Assurance Sampling and Testing Corrosion and Heat-Resistant Steels and Alloys Wrought Products and Forging Stock
AMS2374	Quality Assurance Sampling and Testing Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS2750	Pyrometry
AMS2761	Heat Treatment of Steel Raw Materials
AMS2806	Identification Bars, Wire, Mechanical Tubing, and Extrusions Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification Forgings
AMS7490	Rings, Flash Welded Corrosion and Heat-Resistant Austenitic Steels, Austenitic-Type Iron, Nickel, or Cobalt Alloys, or Precipitation-Hardenable Alloys

- ARP1110 Minimizing Stress Corrosion Cracking in Wrought Forms of Steels and Corrosion Resistant Steels and Alloys
- ARP1917 Clarification of Terms Used in Aerospace Metals Specifications
- AS1182 Standard Stock Removal Allowance Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing
- AS6279 Industry Standard Practices for Production, Distribution, and Procurement of Metal Stock

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

- ASTM A370 Mechanical Testing of Steel Products
- ASTM A604 Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
- ASTM A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products
- ASTM E112 Determining Average Grain Size
- ASTM E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM A751, or by other analytical methods acceptable to purchaser.

**Table 1 - Composition**

Element	Min	Max
Carbon	--	0.05
Manganese	--	0.10
Silicon	--	0.10
Phosphorus	--	0.010
Sulfur	--	0.008
Chromium	12.25	13.25
Nickel	7.50	8.50
Molybdenum	2.00	2.50
Aluminum	0.90	1.35
Nitrogen	--	0.010

#### 3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248 except that no variation over maximum is permitted for nitrogen.

#### 3.2 Melting Practice

Product shall be multiple melted using vacuum induction primary melting followed by either vacuum consumable electrode remelting for Type 1 or, when specified, electroslag remelting for Type 2.