



# AEROSPACE MATERIAL SPECIFICATION

AMS5844™

REV. J

Issued	1972-11
Reaffirmed	2007-08
Revised	2019-07

Superseding AMS5844H

Alloy, Corrosion-Resistant, Round Bars  
20Cr - 35Ni - 35Co - 10Mo  
Vacuum Induction Plus Consumable Electrode Vacuum Remelted  
Solution Heat Treated and Work Strengthened  
(Composition similar to UNS R30035)

## RATIONALE

AMS5844J prohibits unauthorized exceptions (3.8), revises properties (3.5.2.1), reports (4.4), and identification (5.2.1.1), and results from a Five-Year Review and update of this specification.

### 1. SCOPE

#### 1.1 Form

This specification covers a high-strength, corrosion-resistant alloy in the form of bars up to 1.75 inches (44.4 mm) in diameter (see 8.2 and 8.7).

#### 1.2 Application

These bars have been used typically for applications requiring a combination of high strength, good tension-tension fatigue strength, toughness, ductility, and exceptionally good corrosion resistance after aging (see 8.2), but usage is not limited to such applications.

### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

#### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2261 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire

AMS2269 Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2019 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
<http://www.sae.org>

SAE WEB ADDRESS:

SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://standards.sae.org/AMS5844J>

AMS2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS2750	Pyrometry
AMS2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM E8/E8M	Tension Testing of Metallic Materials
ASTM E18	Rockwell Hardness of Metallic Materials
ASTM E112	Determining Average Grain Size
ASTM E140	Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness
ASTM E354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

**Table 1 - Composition**

Element	Min	Max
Carbon	--	0.025
Manganese	--	0.15
Silicon	--	0.15
Phosphorus	--	0.015
Sulfur	--	0.010
Chromium	19.00	21.00
Nickel	33.00	37.00
Molybdenum	9.00	10.50
Titanium	--	1.00
Iron	--	1.00
Cobalt	remainder	

#### 3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2269.

### 3.2 Melting Practice

Alloy shall be multiple melted using vacuum induction melting followed by consumable electrode vacuum remelting.