
**Epoxidized natural rubber —
Determination of epoxidation and ring
opening level by NMR spectrometry**

*Caoutchouc naturel époxydé — Détermination de l'époxydation et du
niveau d'ouverture des anneaux par spectrométrie RMN*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Reagents.....	2
6 Apparatus.....	2
7 Procedure.....	2
7.1 Sample preparation.....	2
7.2 NMR measurement.....	3
8 Calculation.....	3
9 Precision.....	3
10 Test report.....	3
Annex A (informative) ¹H NMR spectra of ENR 25 and ENR 50.....	5
Annex B (informative) Precision.....	6
Bibliography.....	9