



AEROSPACE MATERIAL SPECIFICATION

AMS2615™

REV. G

Issued 1945-08
Reaffirmed 2018-08
Revised 2023-05

Superseding AMS2615F

Pressure Testing, Hydraulic
Pressure as Specified

RATIONALE

Five-Year Review and update of this specification resulted in clarifications to classes (1.2) and to leakage (3.5.1).

1. SCOPE

1.1 Application

This specification provides requirements and procedures for hydraulic-pressure leak testing of parts.

1.2 Classification

The following classes of tests establish the allowable leakage:

- Class A - No visible leakage permitted
- Class B - Up to 2 mL/min
- Class C - Up to 2 mL/min for any area bounded by a 1-inch (25-mm) diameter circle
- Class D - Very slow leak which allows the surface to become slightly moist or damp
- Class E - A specified leakage rate

1.2.1 If a class is not specified, Class A shall apply.

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS2615G/>

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AS7766 Terms Used in Aerospace Metals Specifications

3. TECHNICAL REQUIREMENTS

3.1 Equipment

3.1.1 Fixtures

Test fixtures and apparatus shall be designed and constructed to seal off only the ports and passages required to pressurize the part, and to permit 100% evaluation of all areas of the part where leakage could occur. The design shall not induce any stress on the part other than that provided by the test media. If pressure testing cannot be accomplished without inducing additional stresses, the design, including fitting types, shall be approved by the cognizant engineering organization.

3.1.2 Gaskets

Gasket material shall be used with plugs or blanking plates to prevent damage to finished surfaces when sealing. Flanges or fittings designed for use with specific O-rings or gaskets shall use those for test. Formed-in-place gaskets that could mask dimensional or surface flaws shall not be used except for unmachined castings.

3.1.3 Bleeder Ports

Valved bleeder ports shall be provided to release entrapped air.

3.1.4 Instruments

Pressure gauges and flow meters shall have sufficient dial divisions or readability to permit monitoring of specified pressure, with maximum gauge capacity not more than five times test pressure and readability not less than 5% of test pressure. Gauges shall have been calibrated, within 1 year of use, using either primary standards or standards traceable to the National Institute of Standards and Technology.

3.1.5 Safety Tank or Screen

A suitable tank or screen shall be provided to protect the operator in case of failure of a part (see 8.2).

3.1.6 Drying Oven

A circulating-air oven shall be used for drying parts subject to corrosion.

3.2 Test Media

Water, hydraulic fluid, or suitable petroleum-based test media shall be used. The test media shall be inert to the part and shall have a viscosity of 25 centistokes or less.