



Designation: C31/C31M – 24

# Standard Practice for Making and Curing Concrete Test Specimens in the Field<sup>1</sup>

This standard is issued under the fixed designation C31/C31M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This practice covers procedures for making and curing cylinder and beam specimens from representative samples of fresh concrete for a construction project.

1.2 This practice is not intended for making specimens from concrete not having measurable slump or requiring other sizes or shapes of specimens.

1.3 This practice is not applicable to lightweight insulating concrete or controlled low strength material (CLSM).

NOTE 1—Test Method C495/C495M covers the preparation of specimens and the determination of the compressive strength of lightweight insulating concrete. Test Method D4832 covers procedures for the preparation, curing, transporting and testing of cylindrical test specimens of CLSM.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. (Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to exposed skin and tissue upon prolonged exposure.<sup>2</sup>)*

1.6 The text of this standard references notes which provide explanatory material. These notes shall not be considered as requirements of the standard.

1.7 *This international standard was developed in accordance with internationally recognized principles on standard-*

*ization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>3</sup>

- C94/C94M Specification for Ready-Mixed Concrete
- C125 Terminology Relating to Concrete and Concrete Aggregates
- C138/C138M Test Method for Density (Unit Weight), Yield, and Air Content (Gravimetric) of Concrete
- C143/C143M Test Method for Slump of Hydraulic-Cement Concrete
- C172/C172M Practice for Sampling Freshly Mixed Concrete
- C173/C173M Test Method for Air Content of Freshly Mixed Concrete by the Volumetric Method
- C231/C231M Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method
- C330/C330M Specification for Lightweight Aggregates for Structural Concrete
- C403/C403M Test Method for Time of Setting of Concrete Mixtures by Penetration Resistance
- C470/C470M Specification for Molds for Forming Concrete Test Cylinders Vertically
- C495/C495M Test Method for Compressive Strength of Lightweight Insulating Concrete
- C511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes
- C617/C617M Practice for Capping Cylindrical Concrete Specimens
- C1064/C1064M Test Method for Temperature of Freshly Mixed Hydraulic-Cement Concrete
- C1077 Practice for Agencies Testing Concrete and Concrete Aggregates for Use in Construction and Criteria for Testing Agency Evaluation

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.61 on Testing for Strength.

Current edition approved Jan. 1, 2024. Published February 2024. Originally approved in 1920. Last previous edition approved in 2023 as C31/C31M–23. DOI: 10.1520/C0031\_C0031M-24.

<sup>2</sup> See Section on Safety Precautions, Manual of Aggregate and Concrete Testing, *Annual Book of ASTM Standards*, Vol. 04.02.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

**C1611/C1611M** Test Method for Slump Flow of Self-Consolidating Concrete

**C1758/C1758M** Practice for Fabricating Test Specimens with Self-Consolidating Concrete

**D4832** Test Method for Preparation and Testing of Controlled Low Strength Material (CLSM) Cylindrical Test Specimens

2.2 American Concrete Institute Publication:<sup>4</sup>

**309R** Guide for Consolidation of Concrete

### 3. Terminology

#### 3.1 Definitions:

3.1.1 For definitions of terms used in this practice, refer to Terminology **C125**.

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *acceptance test specimens, n*—standard-cured test specimens intended for evaluating whether the supplied concrete complies with the specification.

3.2.2 *field-curing, n*—storing test specimens in the field under an environmental temperature and moisture environment similar to the in-place concrete.

3.2.3 *initial-curing, n*—the storage of test specimens in the field after molding and before transporting the specimens to the laboratory.

3.2.3.1 *Discussion*—Initial curing covers the time period from molding to transporting the test specimens.

3.2.4 *initial standard curing temperature, n*—temperature of the environment surrounding the specimen during initial standard curing.

3.2.4.1 *Discussion*—The environment surrounding standard-cured test specimens may be air, water, or damp sand. The temperature of the environment surrounding standard-cured test specimen might not be the same as the concrete temperature.

3.2.5 *standard-curing, n*—storing test specimens in an environment of a specified temperature range, and under conditions that control the loss of moisture from the test specimens while the test specimens are in the field and while in the laboratory.

3.2.5.1 *Discussion*—Standard-curing is intended to reduce the influence of variations by standardizing the temperature and moisture environment on the strength development of test specimens. Standard-curing includes requirements for the curing environment while the test specimens are in the field (10.1.2) and while the test specimens are in the laboratory (10.1.3).

### 4. Significance and Use

4.1 This practice provides standardized requirements for making, and curing test specimens in the field. This practice also provides requirements for transporting test specimens to the laboratory, and for curing test specimens in the laboratory. Depending on their purpose, test specimens are either standard-cured, or field-cured.

<sup>4</sup> Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.aci-int.org>.

4.2 Uses of the test results of standard-cured test specimens include the following purposes:

4.2.1 Acceptance testing for specified concrete strength,

NOTE 2—Specification **C94/C94M** requires compressive-strength test specimens for acceptance to be standard-cured.

4.2.2 Checking adequacy of mixture proportions for concrete strength, and

4.2.3 Quality control.

4.3 Uses of test results of field-cured test specimens include:

4.3.1 Estimation of the in place concrete strength,

4.3.2 Comparison with test results of standard cured specimens or with test results from various in-place test methods,

4.3.3 Adequacy of curing and protection of concrete in the structure,

4.3.4 Form or shoring removal time requirements, or

4.3.5 Post-tensioning.

### 5. Apparatus

5.1 *Molds, General*—Molds for specimens or fastenings thereto in contact with the concrete shall be made of steel, cast iron, or other nonabsorbent material, nonreactive with concrete containing portland or other hydraulic cements. Molds shall hold their dimensions and shape under all conditions of use. Molds shall be watertight during use as judged by their ability to hold water poured into them. Provisions for tests of water leakage are given in the Test Methods for Elongation, Absorption, and Water Leakage section of Specification **C470/C470M**. A suitable sealant, such as heavy grease, modeling clay, or microcrystalline wax shall be used where necessary to prevent leakage through the joints. Positive means shall be provided to hold base plates firmly to the molds. Reusable molds shall be lightly coated with mineral oil or a suitable nonreactive form release material before use.

5.2 *Cylinder Molds*—Molds for casting concrete test specimens shall conform to the requirements of Specification **C470/C470M**. Cardboard cylinder molds shall not be used for standard-cured specimens.

5.3 *Beam Molds*—Beam molds shall be of the shape and dimensions required to produce the specimens stipulated in 6.2. The inside surfaces of the molds shall be smooth. The sides, bottom, and ends shall be at right angles to each other and shall be straight and true and free of warp. Maximum variation from the nominal cross section shall not exceed 3 mm [ $\frac{1}{8}$  in.] for molds with depth or breadth of 150 mm [6 in.] or more. Molds shall produce specimens at least as long but not more than 2 mm [ $\frac{1}{16}$  in.] shorter than the required length in 6.2.

5.4 *Tamping Rod*—A round, smooth, straight, steel rod with a diameter conforming to the requirements in Table 1. The length of the tamping rod shall be at least 100 mm [4 in.]

**TABLE 1 Tamping Rod Diameter Requirements**

Diameter of Cylinder or Width of Beam mm [in.]	Diameter of Rod mm [in.]
<150 [6]	10 ± 2 [ $\frac{3}{8}$ ± $\frac{1}{16}$ ]
≥150 [6]	16 ± 2 [ $\frac{5}{8}$ ± $\frac{1}{16}$ ]

greater than the depth of the mold in which rodding is being performed, but not greater than 600 mm [24 in.] in overall length (see **Note 3**). The rod shall have the tamping end or both ends rounded to a hemispherical tip of the same diameter as the rod.

**NOTE 3**—A rod length of 400 mm [16 in.] to 600 mm [24 in.] meets the requirements of the following: Practice C31/C31M, Test Method C138/C138M, Test Method C143/C143M, Test Method C173/C173M, and Test Method C231/C231M.

**5.5 Vibrators**—Internal vibrators shall be used. The vibrator frequency shall be at least 150 Hz [9000 vibrations per minute] while the vibrator is operating in the concrete. The diameter of a round vibrator shall be no more than one-fourth the diameter of the cylinder mold or one-fourth the width of the beam mold. Other shaped vibrators shall have a perimeter equivalent to the circumference of an appropriate round vibrator. The combined length of the vibrator shaft and vibrating element shall exceed the depth of the section being vibrated by at least 75 mm [3 in.]. The vibrator frequency shall be checked periodically with a vibrating-reed tachometer or other suitable device.

**NOTE 4**—For information on size and frequency of various vibrators and a method to periodically check vibrator frequency see ACI 309R.

**5.6 Mallet**—A mallet with a rubber or rawhide head weighing 0.6 kg ± 0.2 kg [1.25 lb ± 0.50 lb] shall be used.

**5.7 Placement Tools**—of a size large enough so each amount of concrete obtained from the sampling receptacle is representative and small enough so concrete is not spilled during placement in the mold. For placing concrete in a cylinder mold, the acceptable tool is a scoop. For placing concrete in a beam mold, either a shovel or scoop is permitted.

**5.8 Finishing Tools**—a handheld float or a trowel.

**5.9 Slump Apparatus**—The apparatus for measurement of slump shall conform to the requirements of Test Method C143/C143M.

**5.10 Sampling Receptacle**—The receptacle shall be a suitable heavy gauge metal pan, wheelbarrow, or flat, clean nonabsorbent board of sufficient capacity to allow easy remixing of the entire sample with a shovel or trowel.

**5.11 Air Content Apparatus**—The apparatus for measuring air content shall conform to the requirements of Test Methods C173/C173M or C231/C231M.

**5.12 Temperature Measuring Devices**—The temperature measuring devices shall conform to the applicable requirements of Test Method C1064/C1064M.

## 6. Testing Requirements

**6.1 Cylindrical Specimens**—Compressive or splitting-tensile-strength specimens shall be cylinders cast and allowed

to set in an upright position. The cylinder diameter shall be at least 3 times the nominal maximum size of the coarse aggregate. The length of the cylinder shall be twice the diameter of the cylinder. If the nominal maximum size of the aggregate is 37.5 mm [1½ in.] or larger, acceptance test specimens for compressive strength shall be 150 mm by 300 mm [6 in. by 12 in.] cylinders. If the nominal maximum size of the aggregate is less than 37.5 mm [1½ in.], acceptance test specimens for compressive strength shall be either 150 mm by 300 mm [6 in. by 12 in.] cylinders or 100 by 200 mm [4 in. by 8 in.] cylinders.

**NOTE 5**—See 7.2 for concrete containing coarse aggregate larger than 50 mm [2 in.] nominal maximum size.

**NOTE 6**—If molds in SI units are required and not available, molds of equivalent size in inch-pound units should be permitted. If molds in inch-pound units are required and not available, molds of equivalent size in SI units should be permitted.

**6.2 Beam Specimens**—Flexural strength specimens shall be beams of concrete cast and hardened in the horizontal position. The length shall be at least 50 mm [2 in.] greater than three times the depth as tested. The ratio of width to depth as molded shall not exceed 1.5.

**6.2.1** The minimum cross-sectional dimension of the beam shall be as stated in **Table 2**. Unless otherwise specified by the specifier of tests, the standard beam shall be 150 mm by 150 mm [6 in. by 6 in.] in cross section.

**6.2.2** When the nominal maximum size of the coarse aggregate exceeds 50 mm [2 in.], the concrete sample shall be treated by wet sieving through a 50 mm [2 in.] sieve as described in Practice C172/C172M.

**6.2.3** The specifier of tests shall specify the specimen size and the number of specimens to be tested to obtain an average test result (**Note 7**). The same specimen size shall be used when comparing results and for mixture qualification and acceptance testing.

**NOTE 7**—The modulus of rupture can be determined using different specimen sizes. However, measured modulus of rupture generally increases as specimen size decreases.<sup>5,6</sup> The strength ratio for beams of different sizes depends primarily on the maximum size of aggregate.<sup>7</sup> Experimental data obtained in two different studies have shown that for maximum aggregate size between 19.0 mm and 25.0 mm [¾ in. and 1 in.], the ratio between the modulus of rupture determined with a 150 mm by 150 mm [6 in. by 6 in.] and a 100 mm by 100 mm [4 in. by 4 in.] may vary from 0.90 to 1.07<sup>5</sup> and for maximum aggregate size between 9.5 mm and 37.5 mm [¾ in. and 1½ in.], the ratio between the modulus of rupture determined with a 150 mm by 150 mm [6 in. by 6 in.] and a 115 mm by 115 mm [4.5 in. by 4.5 in.] may vary from 0.86 to 1.00.<sup>6</sup>

<sup>5</sup> Tanesi, J; Ardani, A. Leavitt, J. "Reducing the Specimen Size of Concrete Flexural Strength Test (AASHTO T97) for Safety and Ease of Handling," *Transportation Research Record: Journal of the Transportation Research Board*, No. 2342, Transportation Research Board of National Academies, Washington, D.C., Carrasquillo, P.M. and Carrasquillo, R. L "Improved Concrete Quality Control Procedures Using Third Point Loading", *Research Report 119-1F*, Project 3-9-87-1119, Center for Transportation Research, The University of Texas at Austin, November 1987.

<sup>6</sup> Carrasquillo, P.M. and Carrasquillo, R. L "Improved Concrete Quality Control Procedures Using Third Point Loading", *Research Report 119-1F*, Project 3-9-87-1119, Center for Transportation Research, The University of Texas at Austin, November 1987.

<sup>7</sup> Bazant, Z. and Novak, D. "Proposal for Standard Test of Modulus of Rupture of Concrete with its Size Dependence," *ACI Materials Journal*, January-February 2001.

**TABLE 2 Minimum Cross-Sectional Dimension of Beams**

Nominal Maximum Aggregate Size (NMAS)	Minimum Cross-Sectional Dimension
≤ 25 mm [1 in.]	100 mm by 100 mm [4 in. by 4 in.]
25 mm [1 in.] < NMAS ≤ 50 mm [2 in.]	150 mm by 150 mm [6 in. by 6 in.]