



Designation: E2580 – 24

Standard Practice for Ultrasonic Testing of Flat Panel Composites and Sandwich Core Materials Used in Aerospace Applications¹

This standard is issued under the fixed designation E2580; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This practice covers two procedures for ultrasonic testing (UT) of flat panel (parallel surfaces) composites and flat sandwich core panels. Typical as-fabricated lay-ups include uniaxial, cross ply, and angle ply laminates, as well as honeycomb sandwich core materials. These procedures can be used throughout the life cycle of the materials: product and process design optimization, on line process control, after manufacture inspection, and in-service inspection. Contact methods, such as angle-beam techniques using shear waves, are not discussed.

1.2 Ultrasonic testing is a common subsurface method for detection of laminar discontinuities. Two techniques can be considered based on panel surface accessibility; pulse echo for one sided and through transmission (bubblers/squirters) for two sided. As used in this practice, both require the use of a pulsed straight-beam ultrasonic longitudinal wave followed by observing indications of either the reflected (pulse-echo) or received (through transmission) wave. The general types of anomalies detected by both techniques include foreign materials, delamination, disbond/un-bond, fiber de-bonding, inclusions, porosity, and voids.

1.3 This practice provides two ultrasonic test procedures. These test procedures can be applied to small area manual scanning and large area automated scanning. Each has its own merits and requirements for inspection and shall be selected as agreed upon in a contractual document.

1.3.1 *Test Procedure A, Pulse Echo (Non-contacting and Contacting)*, is at a minimum a single transducer transmitting and receiving a longitudinal wave in the range of 0.5 MHz to 20 MHz (see Fig. 1). This procedure requires access to only one side of the specimen. This procedure can be conducted by automated or manual means. Automated and manual test results may be imaged or recorded.

¹ This practice is under the jurisdiction of ASTM Committee E07 on Nondestructive Testing and is the direct responsibility of Subcommittee E07.06 on Ultrasonic Method.

Current edition approved Feb. 1, 2024. Published March 2024. Originally approved in 2007. Last previous edition approved in 2017 as E2580 – 17. DOI: 10.1520/E2580-24.

1.3.2 *Test Procedure B, Through Transmission*, is a combination of two transducers. One transmits a longitudinal wave and the other receives the longitudinal wave in the range of 0.5 MHz to 20 MHz (see Fig. 2 for an example set-up using squirters). This procedure requires access to both sides of the specimen. This procedure is automated and the examination results are recorded.

1.4 This practice does not specify accept-reject criteria.

1.5 *Units*—The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards*:²

[D3878 Terminology for Composite Materials](#)

[D5687/D5687M Guide for Preparation of Flat Composite Panels with Processing Guidelines for Specimen Preparation](#)


[E317 Practice for Evaluating Performance Characteristics of Ultrasonic Pulse-Echo Testing Instruments and Systems without the Use of Electronic Measurement Instruments](#)

[E543 Specification for Agencies Performing Nondestructive Testing](#)

[E1065/E1065M Practice for Evaluating Characteristics of](#)

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard



Automated

Manual

FIG. 1 Test Procedure A, Example Pulse Echo Apparatus Set-ups




FIG. 2 Test Procedure B, Through Transmission Apparatus Set-up Using Squirters

Ultrasonic Search Units

- E1309 Guide for Identification of Fiber-Reinforced Polymer-Matrix Composite Materials in Databases (Withdrawn 2015)³
- E1316 Terminology for Nondestructive Examinations

- E1324 Guide for Measuring Some Electronic Characteristics of Ultrasonic Testing Instruments
- E1434 Guide for Recording Mechanical Test Data of Fiber-Reinforced Composite Materials in Databases (Withdrawn 2015)³
- E1471 Guide for Identification of Fibers, Fillers, and Core Materials in Computerized Material Property Databases (Withdrawn 2015)³

³ The last approved version of this historical standard is referenced on www.astm.org.

2.2 *SAE Standards*:⁴

ARP 5605 Solid Composite Laminate NDI Reference Standards

ARP 5606 Composite Honeycomb NDI Reference Standards

3. Terminology

3.1 *Definitions*—Terminology in accordance with Terminologies **E1316** and **D3878** shall be used where applicable.

4. Summary of Practice

4.1 This practice describes two procedures for detecting anomalies in flat panel composite and flat sandwich core panels using ultrasonic longitudinal waves coupled by either contact (Procedure A) or bubbler/squitter (Procedure B). Equipment, reference blocks, examination and evaluation procedures, and documentation are described in detail.

5. Significance and Use

5.1 This practice is intended primarily for the testing of flat panel composites and sandwich core panels to an acceptance criteria most typically specified in a purchase order or other contractual document.

5.2 *Basis of Application*—There are areas in this practice that require agreement between the cognizant engineering organization and the supplier, or specific direction from the cognizant engineering organization.

6. Basis of Application

6.1 The following items are subject to contractual agreement between the parties using or referencing this standard.

6.2 *Personnel Qualification*—If specified in the contractual agreement, personnel performing examinations to this standard shall be qualified in accordance with a nationally or internationally recognized NDT personnel qualification practice or standard and certified by the employer or certifying agency, as applicable. The practice or standard used, and its applicable revision, shall be identified in the contractual agreement between the using parties.

6.3 *Qualification of Nondestructive Agencies*—If specified in the contractual agreement, NDT agencies shall be qualified and evaluated as described in Specification **E543**. The applicable edition of Specification **E543** shall be specified in the contractual agreement.

6.4 *Surface Preparation*—The pre-examination surface preparation criteria shall be in accordance with **8.4**, unless otherwise specified.

6.5 *Timing of Examination*—The timing of examination shall be in accordance with **8.2** and **8.3**, unless otherwise specified.

6.6 *Extent of Examination*—The extent of examination shall be in accordance with **8.5** unless otherwise specified.

6.7 *Reporting Criteria/Acceptance Criteria*—Reporting criteria for the examination results shall be in accordance with **14.1** unless otherwise specified. Since acceptance criteria (for example, for reference radiographs) are not specified in this standard, they shall be specified in the contractual agreement.

6.8 *Reexamination of Repaired/Reworked Items*—Reexamination of repaired/reworked items is not addressed in this standard and if required shall be specified in the contractual agreement.

7. Equipment and Materials

7.1 Equipment

7.1.1 *Operation*—Test equipment shall be capable of providing uniform, repeatable, and controlled operation.

7.1.2 *Electronic Equipment*—The electronic equipment should be capable of producing and processing electronic signals at frequencies in the range of search unit frequencies being used.

7.1.3 *Search Unit(s)*—The search unit(s) selected should be compatible with the electronic equipment being used and with the material to be inspected. The search unit should match the intended squitter(s) or contact. Only longitudinal, straight-beam search units, with flat or focused acoustic lenses, should be used.

7.1.4 *Alarm*—The alarm or threshold level should be adjustable to allow triggering at any commonly required level of indication amplitude. Alarms are not required on systems that record amplitude recordings.

7.1.5 *Alarm Gate Synchronization*—In the pulse echo mode, ensure that the alarm gate tracks the inspection area. The gate should lock on the first interface pulse from the test piece rather than on the initial pulse from the system. In the through transmission mode, the alarm gate should be wide enough to cover any negative or positive movement (left to right) in the horizontal plane.

7.1.6 *Manipulating Equipment* should be provided to adequately support the search tube(s) and allow angular adjustment in two mutually perpendicular planes. The search unit manipulator shall be capable of providing the adjustments necessary to properly position the search unit during testing. The scanning and indexing apparatus should have sufficient structural rigidity to provide support for the manipulator and should allow smooth, accurate positioning of the search unit. The scanning apparatus should be sufficiently rigid to keep search unit backlash to within tolerances as specified in the contractual agreement.

7.1.7 *Tank or Gantry System*—The tank or gantry system should permit accurate positioning of the search unit, reference standards, and part or material to be examined.

7.1.8 *Squitter*—The squitter equipment shall be capable of supplying a laminar flow of coupling fluid from the transducer to the part being tested at all angles used.

7.1.9 *Scan-Record*—The recording shall not exhibit backlash or hysteresis that would hinder detection or evaluation of discontinuities.

7.1.10 *Composite Reference Blocks*—For the applicable testing system, the responses from reference block(s) and part shall be similar to the extent that standardization of the testing

⁴ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.