



Standard Practice for Calculating Yellowness and Whiteness Indices from Instrumentally Measured Color Coordinates¹

This standard is issued under the fixed designation E313; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This practice provides numbers that correlate with visual ratings of yellowness or whiteness of white and near-white or colorless object-color specimens, viewed in daylight by an observer with normal color vision. White textiles, paints, and plastics are a few of the materials that can be described by the indices of yellowness or whiteness calculated by this practice.

1.2 For a complete analysis of object colors, by a specified observer and under a specified illuminant, use of three parameters is required. For near-white specimens, however, it is often useful to calculate single-number scales of yellowness or whiteness. This practice provides recommended equations for such scales and discusses their derivations and uses, and limits to their applicability (see also Ref (1)²).

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

D1535 Practice for Specifying Color by the Munsell System

D1729 Practice for Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials

D1925 Test Method for Yellowness Index of Plastics⁴

E284 Terminology of Appearance

E308 Practice for Computing the Colors of Objects by Using the CIE System

E805 Practice for Identification of Instrumental Methods of Color or Color-Difference Measurement of Materials

E991 Practice for Color Measurement of Fluorescent Specimens Using the One-Monochromator Method

E1164 Practice for Obtaining Spectrometric Data for Object-Color Evaluation

E1247 Practice for Detecting Fluorescence in Object-Color Specimens by Spectrophotometry

E1331 Test Method for Reflectance Factor and Color by Spectrophotometry Using Hemispherical Geometry

E1345 Practice for Reducing the Effect of Variability of Color Measurement by Use of Multiple Measurements

E1347 Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry

E1348 Test Method for Transmittance and Color by Spectrophotometry Using Hemispherical Geometry

E1349 Test Method for Reflectance Factor and Color by Spectrophotometry Using Bidirectional (45°:0° or 0°:45°) Geometry

E1360 Practice for Specifying Color by Using the Optical Society of America Uniform Color Scales System

E1499 Guide for Selection, Evaluation, and Training of Observers

E1541 Practice for Specifying and Matching Color Using the Colorcurve System⁴

3. Terminology

3.1 Terms and definitions in Terminology **E284** are applicable to this practice.

3.2 *Definitions:*

¹ This practice is under the jurisdiction of ASTM Committee **E12** on Color and Appearance and is the direct responsibility of Subcommittee **E12.04** on Color and Appearance Analysis.

Current edition approved July 1, 2010. Published July 2010. Originally approved in 1967. Last previous edition approved in 2005 as E313 – 05. DOI: 10.1520/E0313-10.

² The boldface numbers in parentheses refer to the list of references at the end of this practice.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

3.2.1 *perfect reflecting diffuser*, *n*—ideal reflecting surface that neither absorbs nor transmits light, but reflects diffusely, with the radiance of the reflecting surface being the same for all reflecting angles, regardless of the angular distribution of the incident light.

3.2.2 *whiteness*, *n*—the attribute of color perception by which an object color is judged to approach the preferred white.

3.2.3 *whiteness index*, *WI*, *n*—a number, computed by a given procedure from colorimetric data, that indicates the degree of departure of an object color from that of a preferred white.

3.2.4 *yellowness*, *n*—the attribute of color perception by which an object color is judged to depart from colorless or a preferred white toward yellow.

3.2.5 *yellowness index*, *YI*, *n*—a number, computed by a given procedure from colorimetric or spectrophotometric data, that indicates the degree of departure of an object color from colorless or from a preferred white, toward yellow.

3.2.5.1 *Discussion*—Negative values of *YI* denote departure toward blue.

3.3 Definitions of Terms Specific to This Practice:

3.3.1 *near white*, *n*—a color having a Munsell value greater than 8.3 (luminous reflectance factor $Y = 63$) and Munsell chroma no greater than 0.5 for *B* hues, 0.8 for *Y* hues, and 0.3 for all other hues.

3.3.2 *preferred white*, *n*—color of a white standard used as the basis for calculating indices of whiteness or yellowness as the departure of the color of the specimen from that of the preferred white; in this practice, the perfect reflecting diffuser.

4. Summary of Practice

4.1 The calculations described in this practice assume that specimens have been measured according to Practices E1164 and E308 and one of the Test Methods E1331, E1347, E1348, or E1349, depending on the type of specimen and measuring instrument used (see also Practice E805).

4.2 This practice takes as a starting point for the calculations CIE tristimulus values *X*, *Y*, and *Z* for one of the CIE standard observers and one of the CIE standard or recommended illuminants of daylight quality. Such tristimulus values are available by use of modern color measuring instruments.

4.3 Equations for the preferred methods of calculating *YI* and *WI* are described in Sections 6 and 7, respectively. Equations for calculating other quantities used as indices of yellowness or whiteness are given in Appendix X1 and Appendix X2, respectively.

5. Significance and Use

5.1 This practice should be used only to compare specimens of the same material and same general appearance. For example, a series of specimens to be compared should have generally similar gloss, texture, and (if not opaque) thickness, and translucency.

5.2 For yellowness measurement, this practice is limited to specimens having dominant wavelength in the range 570 to 580 nm, or Munsell hue approximately 2.5GY to 2.5 Y. For whiteness measurement, this practice is limited to specimens having Munsell value greater than 8.3 (CIE *Y* greater than 65)

and Munsell chroma no greater than 0.5 for *B* hues, 0.8 for *Y* hues, and 0.3 for all other hues (see 3.3.1).

5.3 The combination of measurement and calculation leading to indices of yellowness or whiteness is a psychophysical process, that is, the procedures specified are designed to provide numbers correlating with visual estimates made under specified typical observing conditions. Because visual observing conditions can vary widely, users should compare calculated indices with visual estimates to ensure applicability. Some standards addressing the visual estimation of color and color difference are Practices D1535, D1729, E1360, and E1541, and Guide E1499.

5.4 This practice does not cover the preparation of specimens, a procedure that may affect significantly the quantities measured. In general, specimens should be prepared and presented for measurement in the manner that is standard for the test being performed. Select enough specimens or specimen areas to provide an average result that is representative of each sample to be tested. See Practice E1345.

6. Yellowness Index

6.1 *Background*—The currently recommended equation for the calculation of yellowness index is derived from an equation due to Hunter (2) in 1942: $YI = (A - B)/G$, where *A*, *B*, and *G* are, respectively, amber or red, blue, and green colorimeter readings. Another version, used in the 1940s to 1960s for transparent plastics (3, 4), was based on transmittances near the ends of the visible wavelength region: $YI = 100(T_{680} - T_{420})/T_{560}$ (with a factor of 100 introduced to give values of *YI* near unity). This equation failed to account correctly for differences in the spectral transmittance curves of such plastics, especially after the adoption of ultraviolet light absorbers to improve weathering, and was soon abandoned. When, in 1957, ASTM solicited new equations for calculating yellowness indices, Hunter's equation was converted (5) into CIE tristimulus value form by using Hunter's approximate relations between colorimeter readings and those tristimulus values; the resulting equation, $YI = 100(1.28X - 1.06Z)/Y$, was adopted for use in Test Method D1925 in 1962.

6.1.1 In the original form of Test Method E313, an alternative equation was recommended for a yellowness index. In terms of colorimeter readings, it was $YI = 100(1 - B/G)$. Its derivation assumed that, because of the limitation of the concept to yellow (or blue) colors, it was not necessary to take account of variations in the amber or red colorimeter reading *A*. This equation is no longer recommended.

6.2 *Significant Digits and Precision*—The coefficients of Test Method D1925 equation were rounded to the number of digits shown, commensurate with the precision of then-existing color measurement instrumentation. It was not intended that more significance should be attributed to values of *YI* than that implicit in this number of digits. As instrumentation was improved, however, it was found that some instruments unexpectedly gave nonzero values of *YI* for clear air or the perfect reflecting diffuser. One suggested ((1), p. 205) remedy for this presumed failure of the equation was to increase the number of digits in the numerical coefficients from two to ten after the decimal point, despite the obvious lack of significance of most of these digits. With modern instrumentation, it is believed that