



# Standard Test Method for Adequacy of Fusion of Extruded Poly(Vinyl Chloride) (PVC) Pipe and Molded Fittings by Acetone Immersion<sup>1</sup>

This standard is issued under the fixed designation D 2152; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This test method covers the determination of the adequacy of fusion of extruded rigid poly(vinyl chloride) (PVC) pipe and molded fittings as indicated by reaction to immersion in anhydrous acetone.

1.2 The values stated in inch-pound units are to be regarded as the standard except where instruments are calibrated in SI units.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazards statements are given in [Annex A1](#).

## 2. Referenced Documents

### 2.1 ASTM Standards:

D 618 Practice for Conditioning Plastics for Testing<sup>2</sup>

## 3. Significance and Use

3.1 This test method is applicable only for distinguishing between inadequately fused and adequately fused PVC. The difference between thermally degraded and adequately fused PVC cannot be detected by this test method. Acetone immersion is not a substitute for burst, impact, or other physical or chemical tests on PVC pipe or fittings and it, therefore, shall not be used as the only test specification for purchasing of PVC pipe and fittings. This test only detects inadequate fusion and does not determine the over-all quality of the PVC pipe or fittings.

3.2 This test method is useful in determining whether inadequate fusion contributed to failure of PVC pipe or fittings in other physical or chemical tests, or in service.

3.3 This test method is useful in evaluating the adequacy of PVC fusion obtained in process or materials trials.

3.4 This test method determines adequacy of fusion on a single, relatively small specimen. This test method requires the use of a hazardous reagent which must be properly handled and disposed. Therefore, this test method may not be cost-effective to employ as a routine quality control test.

## 4. Apparatus

4.1 *Container*—Either individual, sealable containers for each specimen or one large, airtight container capable of holding several specimens without touching one another.

4.2 *Hydrometer and Cylinder*—Precision hydrometer, graduated in thousandths, with a minimum range of 0.780 to 0.790 g/mL and a cylinder large enough to immerse the hydrometer.

4.3 *Thermometer*—ASTM 12C total immersion thermometer, range from –20°C to 102°C accurate to 0.2°C, or equivalent.

## 5. Reagent

5.1 *Acetone*—American Chemical Society Reagent Grade, having a maximum density of 0.7857 g/mL at 25°C.

NOTE 1—See [Annex A1](#) for the safety and health precautions to be used with acetone.

5.2 Prior to conducting the test, check the density of the acetone with a precision hydrometer to determine its dryness. If the density of the acetone is greater than 0.7890 g/mL at 23°C, (corresponding to approximately 1 % water by mass (see [Fig. X1.1](#))), use fresh acetone or dry the wet acetone with a drying agent. Recheck the density of the fresh or dried acetone before using.

NOTE 2—Wet acetone can be dried by thoroughly agitating it with at least 15 g of anhydrous calcium sulfate (CaSO<sub>4</sub>) for each gram of water present.

NOTE 3—The presence of water in the acetone reduces its sensitivity to differences in the degree of fusion of rigid poly(vinyl chloride) (PVC). It is important to dry the acetone properly and conduct the test in a sealed container, because acetone rapidly absorbs moisture from the atmosphere.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.25 on Vinyl Based Pipe.

Current edition approved March 15, 1995. Published May 1995. Originally published as D 2152 – 63 T. Last previous edition D 2152 – 80 (1986)<sup>ε1</sup>.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 08.01.