



Standard Practices for Verification and Calibration of Polarimeters¹

This standard is issued under the fixed designation C 1426; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 Polarimeters and polariscopes used for measuring stress in glass are described in Test Methods F 218, C 148, and C 978. These instruments include a light source and several optical elements (polarizers, optical retarders, filters, and so forth) that require occasional cleaning, realigning, and calibration. The objective of these practices is to describe the calibration and verification procedures required to maintain these instruments in calibration and ensure that the optical setup is within specification for satisfactory measurements.

1.2 It is mandatory throughout these practices that both verification and calibration are carried out by qualified personnel who fully understand the concepts used in measurements of stress retardation and are experienced in the practices of measuring procedures described in Test Methods F 218, C 148, and C 978.

2. Referenced Documents

2.1 ASTM Standards:²

- C 148 Test Methods for Polariscopic Examination of Glass Containers
- C 162 Terminology of Glass and Glass Products
- C 770 Test Method for Measurement of Glass Stress—Optical Coefficient
- C 978 Test Method for Photoelastic Determination of Residual Stress in a Transparent Glass Matrix Using a Polarizing Microscope and Optical Retardation Compensation Procedures
- F 218 Test Method for Analyzing Stress in Glass

3. Terminology

3.1 For definitions of terms used in these practices, see Terminology C 162.

¹ These practices are under the jurisdiction of ASTM Committee C14 on Glass and Glass Products and are the direct responsibility of Subcommittee C14.04 on Physical and Mechanical Properties.

Current edition approved Oct. 1, 2004. Published November 2004.

Originally approved in 1999. Last previous addition approved in 1999 as C1426-99.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Principles of Verification and Calibration Procedures

4.1 Verification and calibration of polarimeters are accomplished using the following procedures:

4.1.1 *Procedure A: (Verification)*—Measure individual components and their orientation to ensure that the requirements of Test Methods F 218, C 148, and C 978 are satisfied.

4.1.2 *Procedure B: (Calibration)*—Determine the accuracy of the polarimeter using a calibrated gage or retarder.

5. Auxiliary Component Requirements

5.1 The following are required to verify and calibrate a polarimeter:

5.1.1 *Verification of Components (Procedure A):*

5.1.1.1 *Verification of Polarization Efficiency*, a light-intensity meter, linear over the range of measured values.

5.1.1.2 *Verification of Quarter-Wave Plate*, a Babinet compensator equipped polarimeter, with a monochromatic light source of traceable wavelength.

5.1.1.3 *Reference Polarizer with Known Axis.*

5.1.2 *Calibration of Polarimeter (Procedure B):*

5.1.2.1 Procedure B requires a gage with a calibrated, known retardation. The calibrated gage must have sufficient retardation to calibrate the instrument within its intended use range. For example, a polariscope/polarimeter used in Test Methods C 148 should be calibrated using a gage exhibiting a retardation range of from 0 to 227 nm (0 to 10 temper grade).

5.1.2.2 Alternately, a rectangular cross-section specimen prepared from an SRM glass having a known stress-optical constant, subjected to uniaxial compression in a calibrated testing machine, may be used instead of a calibrated gage with known retardation.

6. Verification and Calibration Procedures

6.1 *Procedure A—Verification and Aligning of Components:*

6.1.1 *Verification of Polarization Efficiency*—Using a light-intensity meter, measure the light intensity, with polarizers crossed (dark field) and then with polarizers parallel, I_p . Calculate the polarization efficiency, E , as follows:

$$E = \frac{(I_p - I_c)}{I_p} \quad (1)$$

The efficiency must satisfy the requirements of the test method for which the polarimeter is used for.