



# Standard Test Method for Tensile Properties of Fiber Reinforced Metal Matrix Composites<sup>1</sup>

This standard is issued under the fixed designation D 3552; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This test method covers the determination of the tensile properties of metal matrix composites reinforced by continuous and discontinuous high-modulus fibers. Nontraditional metal matrix composites as stated in 1.1.6 also are covered in this test method. This test method applies to specimens loaded in a uniaxial manner tested in laboratory air at either room temperature or elevated temperatures. The types of metal matrix composites covered are:

1.1.1 *Unidirectional*—Any fiber-reinforced composite with all fibers aligned in a single direction. Continuous or discontinuous reinforcing fibers, longitudinal and transverse properties.

1.1.2 *0°/90° Balanced Crossply*—A laminate composed of only 0 and 90° plies. This is not necessarily symmetric, continuous, or discontinuous reinforcing fibers.

1.1.3 *Angleply Laminate*—Any balanced laminate consisting of  $\pm$  theta plies where theta is an acute angle with respect to a reference direction. Continuous reinforcing fibers without 0° reinforcing fibers (that is, ( $\pm 45$ )ns, ( $\pm 30$ )ns, and so forth).

1.1.4 *Quasi-Isotropic Laminate*—A balanced and symmetric laminate for which a constitutive property of interest, at a given point, displays isotropic behavior in the plane of the laminate. Continuous reinforcing fibers with 0° reinforcing fibers (that is, (0/ $\pm 45$ /90)s, (0/ $\pm 30$ )s, and so forth).

1.1.5 *Unoriented and Random Discontinuous Fibers*.

1.1.6 *Directionally Solidified Eutectic Composites*.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are provided for information purposes only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

D 3878 Terminology for Composite Materials

E 4 Practices for Force Verification of Testing Machines

E 8 Test Methods for Tension Testing of Metallic Materials

E 83 Practice for Verification and Classification of Extensometer Systems

E 177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

E 456 Terminology Relating to Quality and Statistics

E 1012 Practice for Verification of Test Frame and Specimen Alignment Under Tensile and Compressive Axial Force Application

## 3. Terminology

3.1 *Definitions*—Terminology D 3878 defines terms relating to high-modulus fibers and their composites. Terminology E 6 defines terms relating to mechanical testing. Terminology E 456 and Practice E 177 define terms relating to statistics. In the event of a conflict between terms, Terminology D 3878 shall have precedence over the other standards.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *continuous fiber, n*—a polycrystalline or amorphous fiber that is continuous within the sample or component or that has ends outside of the stress fields under consideration.

3.2.2 *discontinuous fiber, n*—a polycrystalline or amorphous fiber that is discontinuous within the sample or component or that has its ends inside the stress fields under consideration.

## 4. Summary of Test Method

4.1 A tension specimen is mounted in the grips of a mechanical testing machine and monotonically loaded, in tension, at a constant loading rate until specimen failure occurs. The ultimate strength of the material can be determined from the maximum load carried before failure. If the coupon strain

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D30 on Composite Materials and is the direct responsibility of Subcommittee D30.04 on Lamina and Laminate Test Methods.

Current edition approved May 1, 2007. Published June 2007. Originally approved in 1977. Last previous edition approved in 2002 as D 3552 – 96 (2002).

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

is monitored with strain or displacement transducers, then the stress-strain response of the material can be determined, from which the ultimate tensile strain, proportional limit, and tensile modulus of elasticity can be derived.

## 5. Significance and Use

5.1 This test method is designed to produce tensile property data for material specifications, research and development, quality assurance, and structural design and analysis. Factors that influence the tensile response and should be reported include the following: material, methods of material preparation and lay-up, specimen stacking sequence, specimen preparation, specimen conditioning, environment of testing, specimen alignment and gripping, speed of testing, time at temperature, and volume percent reinforcement. Properties, in the test direction, which may be obtained from this test method include the following:

- 5.1.1 Ultimate tensile strength,
- 5.1.2 Ultimate tensile strain,
- 5.1.3 Tensile modulus of elasticity, and
- 5.1.4 Poissons ratio.

## 6. Interferences

6.1 Tension test data are used as the principal criteria for the engineering design in actual structural applications. Therefore, it is important to define test conditions that will produce realistic tensile properties, including statistical variation. Such data will allow the design engineer to determine the most appropriate and meaningful margin of safety. The following test method issues will cause significant data scatter:

6.1.1 *Material and Specimen Preparation*—Poor material fabrication practices, lack of control of fiber alignment, and damage induced by improper coupon machining are known causes of high material data scatter in composites.

6.1.2 *Gripping*—A high percentage of grip-induced failures, especially when combined with high material data scatter, is an indicator of specimen gripping problems.

6.1.3 *System Alignment*—Excessive bending will cause premature failure, as well as highly inaccurate modulus of elasticity determination. Every effort should be made to eliminate excess bending from the test system. Bending may occur as a result of misaligned grips or from specimens themselves if improperly installed in the grips or out of tolerance as a result of poor specimen preparation. If there is any doubt as to the alignment inherent in a given test machine, then the alignment should be checked.

## 7. Apparatus

7.1 *Micrometers*, suitable for reading to within 1 % of the sample width and thickness. For typical specimen geometries, an instrument with an accuracy of  $\pm 2.5 \mu\text{m}$  ( $\pm 0.0001$  in.) is adequate for thickness measurement, while an instrument with an accuracy of  $\pm 25 \mu\text{m}$  ( $\pm 0.001$  in.) is adequate for width measurement.

7.2 *Testing Machine*, comprised of the following:

7.2.1 *Fixed Member*—A fixed or essentially stationary member carrying one grip.

7.2.2 *Movable Member*—A movable member carrying a second grip.

7.2.3 *Loading Mechanism*—A loading mechanism for imparting to the movable member a controlled velocity with respect to the stationary member, this velocity to be regulated as specified in Section 10.

7.2.4 *Load Indicator*—A suitable load-indicating mechanism capable of showing the total load carried by the test specimen. This mechanism shall be essentially free of inertia lag at the specified rate of testing and shall indicate the load with an accuracy of  $\pm 1$  % of the indicated value, or better. The accuracy of the testing machine shall be verified in accordance with Practice E 4. Further, the calibrated load range used for a particular test shall be chosen to ensure the anticipated maximum loads are between 20 to 80 % of the calibrated load range. This is to ensure a linear calibrated load response and protect the load indicator from overload conditions.

7.2.5 *Grips*:

7.2.5.1 *General*—Grip designs shall be suited to the specimens being tested. The grip designs described in Test Methods E 8 shall be applicable but should be sized according to the specimen dimensions.

7.2.5.2 *Grips for Round Specimen*—The grips for round specimens shall be standard threaded grips or split-shoulder grips with shoulder surfaces designed to mate with corresponding specimens described in Section 8. The grips shall be self-aligning.

7.2.5.3 *Grips for Flat Specimens*—The grips shall be wedge-type grips or lateral pressure grips with serrated or knurled surfaces for contact with the specimen. The grips shall be self-aligning; that is, they shall be attached to their respective fixed and movable members in such a manner that when any load is applied, the grips will place the axis of a correctly mounted specimen in coincidence with the applied load direction such that no significant moment is placed on the specimen test section, either in the thickness or width direction. The lateral pressure that is imposed by the wedge-type grips or applied by the lateral pressure grips shall be sufficient to prevent slippage between the grip face and the specimen tab surface without causing excessive lateral compressive damage to the specimen. If the serrations are too coarse, emery cloth or similar materials may be used to distribute the gripping force more uniformly over a larger area of the specimen tab. The serrations shall be maintained clean and care shall be taken to maintain specimen alignment during installation.

7.2.5.4 *Grip Alignment*—To ensure a uniform axial tensile stress state within the specimen test section, the following grip alignment criteria shall be maintained. Test systems shall be aligned according to Test Methods E 1012. The alignment specimen shall be aligned such that the maximum percent bending throughout the test section, determined at an applied average strain of  $500 \mu\epsilon$ , shall not exceed 10 %, and the maximum measured strain from any of the strain gages on the alignment specimen, as a result of gripping stresses at zero applied load, shall not exceed  $50 \mu\epsilon$ .

7.2.6 *Strain*—Strain should be determined by means of either strain gages or an extensometer.

7.2.6.1 *Strain Gages*—The strain gage should be not less than 3 mm in length for the longitudinal direction and not less than 1.5 mm in length for the transverse direction. The gages,

surface preparation, and bonding agents should be chosen to provide for adequate performance on the subject materials and suitable strain-recording equipment shall be used.

7.2.6.2 *Extensometers*—Extensometers used for composite specimen shall satisfy Practice E 83, Class B-1 requirements can be used in place of strain gages for 25-mm (1-in.) gage length specimens or exclusively for high-temperature tests beyond the range of strain gage applications. Extensometers shall be calibrated periodically in accordance with Method E 83.

## 8. Test Specimens

### 8.1 General:

8.1.1 *Test Specimen Size*—Within the limitations of material availability and economy, the specimens shall be sized large enough to be statistically representative of the material to provide meaningful data and, where possible, large enough to affix strain gages or extensometers. Gage lengths incorporating deformation-measuring devices shall be at least 13 mm (½ in.) in length.

NOTE 1—Nonstandard subscaled specimen geometries are supplied for applications in which material size limitations preclude a 13-mm (½-in.) gage length. These geometries are useful in material development studies but are not considered as a standard. Test data from these nonstandard specimens shall be evaluated and reported separately in light of their size limitation.

8.1.2 *Specimen Preparation*—Mechanical property determinations of metal matrix composite specimens are particularly sensitive to the effects of improper specimen preparation methods. Great care should be exercised, especially in machining or trimming. Diamond grinding, water jet cutting, or electrical discharge machining (EDM) shall be used. Obtain final dimensions by water-lubricated precision diamond grinding. The depth of diamond grinding required should be determined through careful examination of the as-machined surfaces. Edges should be flat and parallel within the specified tolerances. Grinding must be conducted with adequate precautions to minimize damaging vibrations. In the EDM method, the sample must be suitably mounted for good electrical contact to prevent extraneous arcing and specimen damage. Surface finishing may be accomplished chemically by slight matrix etching or manually by light sanding or filing.

8.1.3 *Specimen Cross Section*—The cross section of the specimen shall be uniform over the gage length. A slight, gradual taper can be tolerated, provided that the minimum section is at the mid length of the gage length and symmetrical with respect to its centerline. In round specimens, the taper shall be limited to a 0.5 % difference in the diameter between the mid length and the ends of the gage length. In flat specimens, the taper shall not exceed 1 % in the width of the test section. The thickness shall not be tapered. To be statistically representative of the material, a minimum of 200 continuous filaments, chopped fibers, or both, is suggested in composites that are oriented in the direction of the load.

8.2 *Flat Specimens*—The standard dimensions of flat specimens are shown in Fig. 1 and are discussed in subsequent sections in terms of the volume fraction and placement geometry of the reinforcement.

#### 8.2.1 *Unidirectional and Crossply Laminate Composites:*

8.2.1.1 *Longitudinal Specimens*—The test specimens for unidirectional and crossply laminate composites tested in the axial direction are shown in Fig. 1, Design A, B, C, D, or E. If necessary to transition the load into the specimen, or to prevent gripping damage to the filaments near the surface, tabs can be bonded onto the specimen gripping section. The tab length shall be long enough to provide a shear area,  $2W_T L_T$  at each end of the specimen, which is large enough to transfer the maximum load to the specimen. For all but the shortest specimen length, the radius of the curvature of the shoulder should be at least 25 mm (1 in.), and if practical, the edge of the shoulder should be a straight line joining the arc segment and the corner of the tab section. The recommended standard designs for axial specimens of unidirectional and crossply laminate composites are Designs A and B. Designs C, D, and E are considered standard designs when composite material size limitations are encountered. As stated in Note 1, for size-limited panels or blanks used in materials development studies, a nonstandard subscaled specimen (Design F) may be used. Further size limitations (for example, whisker-reinforced composite blanks) will require small specimens, and a standard design is not offered here. Any deviation of specimen geometry from the listed standards or the use of Design F (or any other nonstandard small specimen design) shall be noted in the data summary.

8.2.1.2 *Transverse Specimens*—Transverse strengths of unidirectional composites are low, and larger widths are required to obtain representative and reproducible data. Specimens for such data shall use either Design A or F. However, Design A is the preferred specimen geometry for transverse specimens. Where the length of available composite material direction does not permit a 76-mm (3-in.) specimen (Design G), the gage section may be reduced to a 13-mm (0.5-in.) length. In such cases, the active region of a strain gage, when used, must be placed accurately within the gage length. Any deviation of specimen geometry from the listed standards or the use of Design G (or any other nonstandard small specimen design) shall be noted in the data summary.

#### 8.2.2 *Angleply and Quasi-Isotropic Laminate Composites:*

8.2.2.1 *Specimens*—The test specimens for angleply and quasi-isotropic laminate composites tested in the axial direction are shown in Fig. 1, Design H, I, J, and K. If necessary, to transition the load into the specimen, or to prevent gripping damage to the filaments near the surface, tabs can be bonded onto the specimen gripping section. The tab length shall be long enough to provide a shear area,  $2W_T L_T$  at each end of the specimen, which is large enough to transfer the maximum load to the specimen. The recommended designs for axial specimens of angleply and quasi-isotropic laminate composites are Designs H and I for composites with ply orientations of 45 and 30°, respectively. If other ply orientations are to be tested, the maximum gage width can be calculated by:  $W_{Gmax} = \tan \theta (L_G)$ . Any deviation of specimen geometry from the listed standards or the use of another nonstandard specimen design shall be noted in the data summary.

#### 8.3 *Round Specimens:*

8.3.1 *General*—Metal matrix composites fabricated by the various liquid infiltration and other techniques that produce