

## DIN EN 12497



ICS 67.250; 85.060

Supersedes DIN V ENV 12497,  
July 1998 edition.

Paper and board

## Paper and board intended to come into contact with foodstuffs

Determination of mercury in an aqueous extract

English version of DIN EN 12497

Papier und Pappe – Papier und Pappe für den Kontakt mit Lebensmitteln –  
Bestimmung von Quecksilber in einem wässrigen Extrakt**National foreword**

This standard has been prepared by CEN/TC 172 'Pulp, paper and board' (Secretariat: Germany).

The leading committee within CEN/TC 172 was WG 3 'Analytical methods of the assessment of paper and board in contact with foodstuffs' (Chairmanship: Austria).

The responsible German bodies involved in its preparation were the *Normenausschuss Materialprüfung* (Materials Testing Standards Committee) and the *Normenausschuss Papier und Pappe* (Paper and Board Standards Committee), Technical Committee NMP 421/NPa *Chemisch-technologische Prüfverfahren für Papier, Pappe, Faserstoff und Chemiezellstoff*.

**Amendments**

This standard differs from DIN V ENV 12497, July 1998 edition, as follows:

- a) The status of the standard has been changed to that of a European Standard.
- b) The 'Precision' clause has been amended.
- c) The standard has been editorially revised.

**Previous edition**

DIN V ENV 12497: 1998-07

Document comprises 9 pages.

**English version**

Paper and board

**Paper and board intended to come into contact with foodstuffs  
Determination of mercury in an aqueous extract**

Papiers et cartons – Papiers et cartons destinés à entrer en contact avec des denrées alimentaires – Détermination du mercure dans un extrait aqueux

Papier und Pappe – Papier und Pappe für den Kontakt mit Lebensmitteln – Bestimmung von Quecksilber in einem wässrigen Extrakt

This European Standard was approved by CEN on 2005-06-27.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland, and the United Kingdom.

**CEN**

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## Contents

Page

Foreword .....	3
1 Scope .....	4
2 Normative references .....	4
3 Principle.....	4
4 Reagents.....	4
4.1 General .....	4
4.2 Nitric acid (HNO <sub>3</sub> ), 65 % ( <i>d</i> = 1,42).....	4
4.2.1 Nitric acid (4.2), diluted 1 : 1 (V/V) with water .....	4
4.2.2 Nitric acid (4.2), diluted to 1,5 % (V/V) with water .....	4
4.3 Potassium permanganate (KMnO <sub>4</sub> ), 5 % aqueous solution ( <i>m/V</i> ) .....	4
4.4 Mercury, stock solution, 1000 mg/l.....	4
4.5 Sulphuric acid (H <sub>2</sub> SO <sub>4</sub> ), ( <i>d</i> = 1,84).....	5
4.6 Potassium dichromate (K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub> ), 50 g/l in sulphuric acid solution .....	5
4.7 Hydroxylammonium chloride (HONH <sub>3</sub> Cl), 20 g/l aqueous solution .....	5
4.8 Reducing solutions.....	5
4.8.1 Tin (II) chloride (SnCl <sub>2</sub> · 2H <sub>2</sub> O), 50 g/l in 10 % hydrochloric acid (4.9.1) .....	5
4.8.2 Sodium tetrahydroborate (NaBH <sub>4</sub> ), 0,2 g/l in 0,05 % sodium hydroxide solution (4.10) .....	5
4.9 Hydrochloric acid (HCl), 36 % ( <i>d</i> = 1,19).....	5
4.9.1 Hydrochloric acid (4.9) (HCl), diluted 10 % (V/V) .....	5
4.10 Sodium hydroxide (NaOH), 0,05 % aqueous solution ( <i>m/V</i> ) .....	5
5 Apparatus .....	5
5.1 General .....	5
5.2 General laboratory equipment .....	5
5.3 Volumetric flasks, 100 ml .....	5
5.4 Analytical balance, accuracy 0,1 mg .....	5
5.5 Pipettes from 100 µl to 10 ml, glass or plastics, (high density polyethylene/polypropylene).....	5
5.6 Atomic absorption spectrometer with an appropriate detection system and sensitivity.....	6
6 Preparation of sample .....	6
7 Procedure .....	6
7.1 General .....	6
7.2 Preparation of reference solution .....	6
7.3 Determination of mercury.....	6
7.3.1 General .....	6
7.3.2 Standard additions.....	7
7.4 Determination of blank value .....	7
8 Expression of results.....	7
9 Precision.....	8
10 Test report .....	8