



INTERNATIONAL STANDARD ISO 15360-2:2001
TECHNICAL CORRIGENDUM 1

Published 2007-06-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Recycled pulps — Estimation of Stickies and Plastics —
Part 2:
Image analysis method

TECHNICAL CORRIGENDUM 1

Pâtes recyclées — Estimation des matières collantes et des matières plastiques —

Partie 2: Méthode par analyse d'image

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to ISO 15360-2:2001 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 5, *Test methods and quality specifications for pulps*.

Page 3

In 5.4, add the following note.

NOTE The calibration method uses dark spots on a white background but this test detects light contraries on the dark background. The effect of this difference is yet unknown.

Replace 5.12 with the following (change underlined).

5.12 Filter washing device (see 10.4.2) to wash the filter with a gentle stream of water at a pressure of about 0,1 MPa (1 bar), flow rate of about 10 l/min and distance of delivery tip from filter of about 180 mm.

ICS 85.040

Ref. No. ISO 15360-2:2001/Cor.1:2007(E)

© ISO 2007 – All rights reserved

Published in Switzerland
Copyright International Organization for Standardization
Provided by IHS under license with ISO

No reproduction or networking permitted without license from IHS

Not for Resale